

LNPTTM LUBRICOMPTTM COMPOUND RL002

RL-4020

REGION AMERICAS

DESCRIPTION

LNP LUBRICOMP RL002 compound is based on Nylon 6/6 resin containing 10% PTFE. Added features of this grade include: Wear Resistant.

GENERAL INFORMATION	
Features	Wear resistant
Fillers	Unreinforced, PTFE
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield	75	MPa	ASTM D638
Tensile Stress, break	74	MPa	ASTM D638
Tensile Strain, yield	13.5	%	ASTM D638
Tensile Strain, break	14.3	%	ASTM D638
Tensile Modulus, 50 mm/min	3080	MPa	ASTM D638
Flexural Stress	112	MPa	ASTM D790
Flexural Modulus	3040	MPa	ASTM D790
Tensile Stress, yield	73	MPa	ISO 527
Tensile Stress, break	73	MPa	ISO 527
Tensile Strain, yield	16.7	%	ISO 527
Tensile Strain, break	17.6	%	ISO 527
Tensile Modulus, 1 mm/min	3000	MPa	ISO 527
Flexural Stress	89	MPa	ISO 178
Flexural Modulus	2840	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	897	J/m	ASTM D4812
Izod Impact, notched, 23°C	32	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	3	J	ASTM D3763
Multiaxial Impact	4	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	55	kJ/m ²	ISO 180/1U

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched 80*10*4 +23°C	5	kJ/m²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	76	°C	ASTM D648
CTE, -40°C to 40°C, flow	8.26E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	8.58E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	8.25E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.57E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	74	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Density	1.19	g/cm³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.94	%	ASTM D570
Mold Shrinkage, flow, 24 hrs ⁽²⁾	2.2	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	2.6	%	ASTM D955
Mold Shrinkage, flow, 24 hrs ⁽²⁾	2.23	%	ISO 294
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	2.59	%	ISO 294
Wear Factor Washer	49	10 ⁻¹⁰ in ⁴ 5-min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.27	-	ASTM D3702 Modified: Manual
Static COF	0.23	-	ASTM D3702 Modified: Manual
Moisture Absorption (23°C / 50% RH)	1.18	%	ISO 62
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	275 – 290	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	80 – 95	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	