

LNPTM LUBRICOMPTM COMPOUND RP002

DESCRIPTION

LNP LUBRICOMP RP002 compound is based on Nylon 6/6 resin containing 10% PTFE/silicone. Added features of this grade include: Internally Lubricated, Wear Resistant.

GENERAL INFORMATION

Features	Wear resistant
Fillers	Unreinforced, PTFE/Silicone
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL⁽¹⁾			
Tensile Stress, yield, 5 mm/min	70	MPa	ISO 527
Tensile Stress, break, 5 mm/min	67	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	7.9	%	ISO 527
Tensile Strain, break, 5 mm/min	17.1	%	ISO 527
Tensile Modulus, 1 mm/min	2800	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	90	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
IMPACT⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	35	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
THERMAL⁽¹⁾			
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	213	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	71	°C	ISO 75/Af
PHYSICAL⁽¹⁾			
Mold Shrinkage, flow ⁽²⁾	1.5	%	SABIC method
Density	1.18	g/cm ³	ISO 1183
INJECTION MOLDING⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	275 – 290	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	80 – 95	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	