

LNPTTM LUBRICOMPTTM COMPOUND RX05495

RFL-4316 EM HS MG MR

DESCRIPTION

LNP LUBRICOMP RX05495 compound is based on Nylon 6/6 resin containing 30% glass bead, glass fiber and 5% graphite powder. Added features of this grade include: Easy Molding, Heat Stabilized, Mold Release, Wear Resistant.

GENERAL INFORMATION	
Features	Good Processability, Heat Stabilized, Wear resistant, Enhanced mold release, Dimensional stability, No PFAS intentionally added
Fillers	Glass Fiber, Glass Bead, Graphite
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport /Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break	117	MPa	ASTM D638
Tensile Strain, break	2.8	%	ASTM D638
Tensile Modulus, 50 mm/min	7990	MPa	ASTM D638
Flexural Stress	173	MPa	ASTM D790
Flexural Modulus	6130	MPa	ASTM D790
Tensile Stress, break	112	MPa	ISO 527
Tensile Strain, break	2.9	%	ISO 527
Tensile Modulus, 1 mm/min	7500	MPa	ISO 527
Flexural Stress	176	MPa	ISO 178
Flexural Modulus	7100	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	667	J/m	ASTM D4812
Izod Impact, notched, 23°C	53	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	10	J	ASTM D3763
Multiaxial Impact	2	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	45	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	255	°C	ASTM D648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 1.82 MPa, 3.2mm, unannealed	233	°C	ASTM D648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	229	°C	ISO 75 /Af
PHYSICAL ⁽¹⁾			
Density	1.38	g/cm ³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.84	%	ASTM D570
Mold Shrinkage, flow, 24 hrs ⁽²⁾	0.5	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	1.5	%	ASTM D955
Mold Shrinkage, flow, 24 hrs ⁽²⁾	0.46	%	ISO 294
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	1.5	%	ISO 294
Density	1.38	g/cm ³	ISO 1183
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	280 – 305	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	