

LNPTTM LUBRICOMPTM COMPOUND RZL16

RFL-4016 M

DESCRIPTION

LNP LUBRICOMP RZL16 compound is based on Nylon 6/6 resin containing 30% milled glass, 5% PTFE. Added features of this grade include: Wear Resistant, Dimensional Control.

GENERAL INFORMATION	
Features	Low Warpage, Wear resistant, Dimensional stability
Fillers	Milled Glass Fiber, PTFE
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport / Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 5 mm/min	63	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	62	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	2.4	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	3.2	%	ASTM D638
Tensile Modulus, 5 mm/min	5420	MPa	ASTM D638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	102	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	4410	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	64	MPa	ISO 527
Tensile Stress, break, 5 mm/min	63	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2	%	ISO 527
Tensile Strain, break, 5 mm/min	3	%	ISO 527
Tensile Modulus, 1 mm/min	5380	MPa	ISO 527
Flexural Stress	90	MPa	ISO 178
Flexural Modulus, 2 mm/min	4500	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	188	J/m	ASTM D4812
Izod Impact, notched, 23°C	32	J/m	ASTM D256
Multiaxial Impact	1	J	ISO 6603
Instrumented Dart Impact Total Energy, 23°C	5	J	ASTM D3763
Izod Impact, unnotched 80°10°4 +23°C	19	kJ/m ²	ISO 180/1U

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched 80*10*4 +23°C	4	kJ/m²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	248	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	215	°C	ASTM D648
CTE, -30°C to 30°C, flow	5.5E-05	1/°C	ASTM D696
CTE, -30°C to 30°C, xflow	6.2E-05	1/°C	ASTM D696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	239	°C	ISO 75/Bf
PHYSICAL ⁽¹⁾			
Specific Gravity	1.4	-	ASTM D792
Density	1.39	g/cm³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.69	%	ASTM D570
Mold Shrinkage, flow, 24 hrs ⁽²⁾	1.8	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	1.4	%	ASTM D955
Wear Factor Washer	44	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified: Manual
Wear Factor Ring	3	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.49	-	ASTM D3702 Modified: Manual
Static COF	0.53	-	ASTM D3702 Modified: Manual
Moisture Absorption (23°C / 50% RH)	0.96	%	ISO 62
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	280 – 305	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	