

LNPTM LUBRILOY™ COMPOUND R2000AXP

DESCRIPTION

LNP LUBRILOY R2000AXP compound is based on Nylon 6/6 resin containing proprietary lubricant. Added features of this grade include: Wear Resistant.

GENERAL INFORMATION	
Features	Wear resistant, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield	82	MPa	ASTM D638
Tensile Stress, break	67	MPa	ASTM D638
Tensile Strain, yield	5.2	%	ASTM D638
Tensile Strain, break	24.4	%	ASTM D638
Tensile Modulus, 50 mm/min	3040	MPa	ASTM D638
Flexural Stress	105	MPa	ASTM D790
Flexural Modulus	2790	MPa	ASTM D790
Tensile Stress, yield	69	MPa	ISO 527
Tensile Stress, break	57	MPa	ISO 527
Tensile Strain, yield	17.2	%	ISO 527
Tensile Strain, break	31.4	%	ISO 527
Tensile Modulus, 1 mm/min	2730	MPa	ISO 527
Flexural Stress	90	MPa	ISO 178
Flexural Modulus	2430	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	NB	J/m	ASTM D4812
Izod Impact, notched, 23°C	64	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	60	J	ASTM D3763
Multiaxial Impact	76	J	ISO 6603
Izod Impact, unnotched 80°10°4 +23°C	137	kJ/m²	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	6	kJ/m²	ISO 180/1A
THERMAL ⁽¹⁾			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 1.82 MPa, 3.2mm, unannealed	58	°C	ASTM D648
CTE, -40°C to 40°C, flow	9.86E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	9.12E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	9.86E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	9.13E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	58	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Density	1.12	g/cm ³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.88	%	ASTM D570
Mold Shrinkage, flow, 24 hrs ⁽²⁾	2.3 – 2.5	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	2.3 – 2.5	%	ASTM D955
Mold Shrinkage, flow, 24 hrs ⁽²⁾	2.31 – 2.52	%	ISO 294
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	2.31 – 2.52	%	ISO 294
Wear Factor Washer	10	10 ⁻¹⁰ in ⁴ -min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.3	-	ASTM D3702 Modified: Manual
Static COF	0.16	-	ASTM D3702 Modified: Manual
Density	1.12	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	1.18	%	ISO 62
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	280 – 305	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	