



LNP™ STAT-KON™ Compound RD000

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound R

Product reorder name: RD000

LNP STAT-KON™ RD000 is a compound based on Nylon 66 resin containing Carbon Powder. Added feature of this material is: Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	680	kgf/cm ²	ASTM D 638
Tensile Strain, break	4.5	%	ASTM D 638
Tensile Modulus, 50 mm/min	32300	kgf/cm ²	ASTM D 638
Flexural Stress	970	kgf/cm ²	ASTM D 790
Flexural Modulus	28100	kgf/cm ²	ASTM D 790
Tensile Stress, break	64	MPa	ISO 527
Tensile Strain, break	7.6	%	ISO 527
Tensile Modulus, 1 mm/min	3100	MPa	ISO 527
Flexural Stress	96	MPa	ISO 178
Flexural Modulus	3000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	108	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	10	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	99	cm-kgf	ASTM D 3763
Multiaxial Impact	38	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	90	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	218	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	94	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.92E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.1E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	7.97E-05	1/°C	ISO 11359-2



LNP™ STAT-KON™ Compound RD000

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, xflow	8.1E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	77	°C	ISO 75/Af
PHYSICAL			
Density	1.19	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.54	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	2.7	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	2.4	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	2.65	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	2.44	%	ISO 294
Moisture Absorption (23°C / 50% RH)	0.96	%	ISO 62
ELECTRICAL			
Surface Resistivity	1.E+02 - 1.E+06	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound RD000

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm