



## LNP™ THERMOCOMP™ Compound RF008XXZ

### Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound RF-1008

Product reorder name: RF008XXZ

LNP THERMOCOMP™ RF008XXZ is a compound based on Nylon 66 resin containing 40% Glass Fiber.

| TYPICAL PROPERTIES <sup>1</sup>         | TYPICAL VALUE | Unit                | Standard    |
|-----------------------------------------|---------------|---------------------|-------------|
| <b>MECHANICAL</b>                       |               |                     |             |
| Tensile Stress, break                   | 1880          | kgf/cm <sup>2</sup> | ASTM D 638  |
| Tensile Strain, break                   | 2.5           | %                   | ASTM D 638  |
| Tensile Modulus, 50 mm/min              | 135600        | kgf/cm <sup>2</sup> | ASTM D 638  |
| Flexural Stress                         | 2800          | kgf/cm <sup>2</sup> | ASTM D 790  |
| Flexural Modulus                        | 106100        | kgf/cm <sup>2</sup> | ASTM D 790  |
| Tensile Stress, break                   | 188           | MPa                 | ISO 527     |
| Tensile Strain, break                   | 2.7           | %                   | ISO 527     |
| Tensile Modulus, 1 mm/min               | 12200         | MPa                 | ISO 527     |
| Flexural Stress                         | 287           | MPa                 | ISO 178     |
| Flexural Modulus                        | 12100         | MPa                 | ISO 178     |
| <b>IMPACT</b>                           |               |                     |             |
| Izod Impact, unnotched, 23°C            | 115           | cm-kgf/cm           | ASTM D 4812 |
| Izod Impact, notched, 23°C              | 11            | cm-kgf/cm           | ASTM D 256  |
| Instrumented Impact Energy @ peak, 23°C | 105           | cm-kgf              | ASTM D 3763 |
| Multiaxial Impact                       | 31            | cm-kgf              | ISO 6603    |
| Izod Impact, unnotched 80*10*4 +23°C    | 74            | kJ/m <sup>2</sup>   | ISO 180/1U  |
| Izod Impact, notched 80*10*4 +23°C      | 13            | kJ/m <sup>2</sup>   | ISO 180/1A  |
| <b>THERMAL</b>                          |               |                     |             |
| HDT, 1.82 MPa, 3.2mm, unannealed        | 252           | °C                  | ASTM D 648  |
| CTE, -40°C to 40°C, flow                | 2.52E-05      | 1/°C                | ASTM E 831  |
| CTE, -40°C to 40°C, xflow               | 5.76E-05      | 1/°C                | ASTM E 831  |
| CTE, -40°C to 40°C, flow                | 2.68E-05      | 1/°C                | ISO 11359-2 |
| CTE, -40°C to 40°C, xflow               | 5.92E-05      | 1/°C                | ISO 11359-2 |



## LNP™ THERMOCOMP™ Compound RF008XXZ

### Americas: COMMERCIAL

| TYPICAL PROPERTIES <sup>1</sup>              | TYPICAL VALUE | Unit              | Standard          |
|----------------------------------------------|---------------|-------------------|-------------------|
| <b>THERMAL</b>                               |               |                   |                   |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm        | >240          | °C                | ISO 75/Af         |
| <b>PHYSICAL</b>                              |               |                   |                   |
| Density                                      | 1.478         | g/cm <sup>3</sup> | ASTM D 792        |
| Moisture Absorption, 50% RH, 24 hrs          | 0.6           | %                 | ASTM D 570        |
| Mold Shrinkage, flow, 24 hrs (5)             | 0.3           | %                 | ASTM D 955        |
| Mold Shrinkage, xflow, 24 hrs (5)            | 1.3           | %                 | ASTM D 955        |
| Mold Shrinkage, flow, 24 hrs (5)             | 0.28          | %                 | ISO 294           |
| Mold Shrinkage, xflow, 24 hrs (5)            | 1.34          | %                 | ISO 294           |
| Density                                      | 1.47          | g/cm <sup>3</sup> | ISO 1183          |
| Moisture Absorption (23°C / 50% RH)          | 0.97          | %                 | ISO 62            |
| <b>FLAME CHARACTERISTICS</b>                 |               |                   |                   |
| UL Compliant, 94HB Flame Class Rating (3)(4) | 1.5           | mm                | UL 94 by SABIC-IP |



**LNP™ THERMOCOMP™ Compound RF008XXZ**

**Americas: COMMERCIAL**

| PROCESSING PARAMETERS       | TYPICAL VALUE | Unit |
|-----------------------------|---------------|------|
| <b>Injection Molding</b>    |               |      |
| Drying Temperature          | 80            | °C   |
| Drying Time                 | 4             | hrs  |
| Maximum Moisture Content    | 0.15 - 0.25   | %    |
| Melt Temperature            | 280 - 305     | °C   |
| Front - Zone 3 Temperature  | 295 - 305     | °C   |
| Middle - Zone 2 Temperature | 280 - 295     | °C   |
| Rear - Zone 1 Temperature   | 265 - 275     | °C   |
| Mold Temperature            | 95 - 110      | °C   |
| Back Pressure               | 0.2 - 0.3     | MPa  |
| Screw Speed                 | 30 - 60       | rpm  |