



LNP™ THERMOCOMP™ Compound RF00ASXZ

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound RF-100-10 HS

Product reorder name: RF00ASXZ

LNP™ THERMOCOMP™ RF00ASXZ is a compound based on Nylon 66 resin containing 50% Glass Fiber. Added feature of this material is: Heat Stabilized.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	1910	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1.8	%	ASTM D 638
Tensile Modulus, 5 mm/min	167000	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	2860	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	150900	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	185	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.8	%	ISO 527
Tensile Modulus, 1 mm/min	15780	MPa	ISO 527
Flexural Stress	272	MPa	ISO 178
Flexural Modulus, 2 mm/min	14420	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	83	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	9	cm-kgf/cm	ASTM D 256
Multiaxial Impact	29	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	88	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	52	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	11	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	257	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	248	°C	ASTM D 648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	256	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	247	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.59	-	ASTM D 792



LNP™ THERMOCOMP™ Compound RF00ASXZ

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Density	1.58	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.48	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.41	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1.1	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.77	%	ISO 62



LNP™ THERMOCOMP™ Compound RF00ASXZ

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm