



LNP™ THERMOCOMP™ Compound RX05494

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound RF-1008 HS

Product reorder name: RX05494

LNP THERMOCOMP RX05494 is a compound based on Nylon 6/6 resin containing 40% Glass Fiber. Added features of this material include: Heat Stabilized.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	2170	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Modulus, 50 mm/min	296800	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	2360	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	64000	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	214	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.7	%	ISO 527
Tensile Modulus, 1 mm/min	30080	MPa	ISO 527
Flexural Stress	315	MPa	ISO 178
Flexural Modulus, 2 mm/min	13020	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	148	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	14	cm-kgf/cm	ASTM D 256
Multiaxial Impact	34	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	171	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	97	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	14	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	260	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	253	°C	ASTM D 648
CTE, -30°C to 30°C, flow	2.4E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	6.E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	258	°C	ISO 75/Bf



LNP™ THERMOCOMP™ Compound RX05494

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	249	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.48	-	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.63	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.1 - 0.3	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.8 - 1	%	ASTM D 955
Density	1.48	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62



LNP™ THERMOCOMP™ Compound RX05494

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm