



LNP™ THERMOCOMP™ Compound RZ006SXP

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound RF-1006 EG HS M

Product reorder name: RZ006SXP

LNP THERMOCOMP RZ006SXP is a compound based on Nylon 66 resin containing 30% Milled Glass. Added feature of this material is: Heat Stabilized.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	610	kgf/cm ²	ASTM D 638
Tensile Strain, break	3.3	%	ASTM D 638
Tensile Modulus, 50 mm/min	50300	kgf/cm ²	ASTM D 638
Flexural Stress	980	kgf/cm ²	ASTM D 790
Flexural Modulus	37300	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	32	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	3	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	118	°C	ASTM D 648
PHYSICAL			
Density	1.42	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	1.4	%	ASTM D 955



LNP™ THERMOCOMP™ Compound RZ006SXP

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm