



LNP* Thermocomp* Compound RF007SXP

Americas: COMMERCIAL

Also known as: LNP* Thermocomp* Compound THERMOCOMP RF-1007 HS

Product reorder name: RF007SXP

LNP* Thermocomp* RF007SXP is a nylon 6/6 containing glass fiber. Characteristics include Heat Stabilizer.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	185	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	185	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2.5	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.5	%	ASTM D 638
Tensile Modulus, 50 mm/min	11380	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	250	MPa	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	249	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	8100	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	185	MPa	ISO 527
Tensile Stress, break, 5 mm/min	185	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2.6	%	ISO 527
Tensile Strain, break, 5 mm/min	2.6	%	ISO 527
Tensile Modulus, 1 mm/min	11170	MPa	ISO 527
Flexural Stress	266	MPa	ISO 178
Flexural Modulus, 2 mm/min	9440	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	788	J/m	ASTM D 4812
Izod Impact, notched, 23°C	78	J/m	ASTM D 256
Multiaxial Impact	3	J	ISO 6603
Instrumented Impact Total Energy, 23°C	9	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	55	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	8	kJ/m ²	ISO 180/1A



LNP* Thermocomp* Compound RF007SXP

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	260	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	252	°C	ASTM D 648
CTE, -30°C to 30°C, flow	2.5E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	7.3E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	258	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	245	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.42	-	ASTM D 792
Density	1.42	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.73	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	0.2 - 0.5	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	1 - 3	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	1	%	ISO 62



LNP* Thermocomp* Compound RF007SXP

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm