



LNP™ LUBRICOMP™ Compound WAL34

Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound WAL-4034

Product reorder name: WAL34

LNP LUBRICOMP WAL34 is a compound based on (PBT resin containing 15% PTFE, 20% Aramid Fiber. Added features of this material include: West Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	460	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	460	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	1.5	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1.5	%	ASTM D 638
Tensile Modulus, 50 mm/min	55900	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	790	kgf/cm ²	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	790	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	44700	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 5 mm/min	44	MPa	ISO 527
Tensile Stress, break, 5 mm/min	44	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	1.3	%	ISO 527
Tensile Strain, break, 5 mm/min	1.3	%	ISO 527
Tensile Modulus, 1 mm/min	4520	MPa	ISO 527
Flexural Modulus, 2 mm/min	4100	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	13	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	3	cm-kgf/cm	ASTM D 256
Multiaxial Impact	9	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	39	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	9	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	3	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	182	°C	ASTM D 648



LNP™ LUBRICOMP™ Compound WAL34

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	215	°C	ASTM D 648
CTE, -30°C to 30°C, flow	5.1E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	8.4E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	206	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	130	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.43	-	ASTM D 792
Density	1.42	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.09	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	1.3	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	2.2	%	ASTM D 955
Wear Factor Washer	6	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Dynamic COF	0.24	-	ASTM D 3702 Modified
Static COF	0.21	-	ASTM D 3702 Modified
Moisture Absorption (23°C / 50% RH)	0.09	%	ISO 62



LNP™ LUBRICOMP™ Compound WAL34

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.05	%
Melt Temperature	240 - 265	°C
Front - Zone 3 Temperature	260 - 270	°C
Middle - Zone 2 Temperature	245 - 255	°C
Rear - Zone 1 Temperature	220 - 230	°C
Mold Temperature	80 - 100	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm