



## LNP™ LUBRICOMP™ Compound WFP36

### Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound WFL-4536

Product reorder name: WFP36

LNP LUBRICOMP™ WFP36 is a compound based on PBT resin containing 30% Glass Fiber, 15% PTFE/Silicone. Added features of this material include: Wear Resistant.

| TYPICAL PROPERTIES <sup>1</sup>         | TYPICAL VALUE | Unit                | Standard    |
|-----------------------------------------|---------------|---------------------|-------------|
| <b>MECHANICAL</b>                       |               |                     |             |
| Tensile Stress, break                   | 1150          | kgf/cm <sup>2</sup> | ASTM D 638  |
| Tensile Strain, break                   | 2.5           | %                   | ASTM D 638  |
| Tensile Modulus, 50 mm/min              | 104800        | kgf/cm <sup>2</sup> | ASTM D 638  |
| Flexural Stress                         | 1970          | kgf/cm <sup>2</sup> | ASTM D 790  |
| Flexural Modulus                        | 89100         | kgf/cm <sup>2</sup> | ASTM D 790  |
| Tensile Stress, break                   | 118           | MPa                 | ISO 527     |
| Tensile Strain, break                   | 2.7           | %                   | ISO 527     |
| Tensile Modulus, 1 mm/min               | 11760         | MPa                 | ISO 527     |
| Flexural Stress                         | 189           | MPa                 | ISO 178     |
| Flexural Modulus                        | 9350          | MPa                 | ISO 178     |
| <b>IMPACT</b>                           |               |                     |             |
| Izod Impact, unnotched, 23°C            | 58            | cm-kgf/cm           | ASTM D 4812 |
| Izod Impact, notched, 23°C              | 7             | cm-kgf/cm           | ASTM D 256  |
| Instrumented Impact Energy @ peak, 23°C | 76            | cm-kgf              | ASTM D 3763 |
| Multiaxial Impact                       | 143           | cm-kgf              | ISO 6603    |
| Izod Impact, unnotched 80*10*4 +23°C    | 46            | kJ/m <sup>2</sup>   | ISO 180/1U  |
| Izod Impact, notched 80*10*4 +23°C      | 10            | kJ/m <sup>2</sup>   | ISO 180/1A  |
| <b>THERMAL</b>                          |               |                     |             |
| HDT, 1.82 MPa, 3.2mm, unannealed        | 213           | °C                  | ASTM D 648  |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm   | 213           | °C                  | ISO 75/Af   |
| <b>PHYSICAL</b>                         |               |                     |             |
| Density                                 | 1.579         | g/cm <sup>3</sup>   | ASTM D 792  |
| Moisture Absorption, 50% RH, 24 hrs     | 0.4           | %                   | ASTM D 570  |
| Mold Shrinkage, flow, 24 hrs (5)        | 0.1 - 0.3     | %                   | ASTM D 955  |



**LNP™ LUBRICOMP™ Compound WFP36**

**Americas: COMMERCIAL**

| TYPICAL PROPERTIES <sup>1</sup>   | TYPICAL VALUE | Unit                                            | Standard             |
|-----------------------------------|---------------|-------------------------------------------------|----------------------|
| <b>PHYSICAL</b>                   |               |                                                 |                      |
| Mold Shrinkage, xflow, 24 hrs (5) | 0.5 - 1       | %                                               | ASTM D 955           |
| Mold Shrinkage, flow, 24 hrs (5)  | 0.1 - 0.3     | %                                               | ISO 294              |
| Mold Shrinkage, xflow, 24 hrs (5) | 0.5 - 1       | %                                               | ISO 294              |
| Wear Factor Washer                | 136           | 10 <sup>-10</sup> in <sup>5</sup> -min/ft-lb-hr | ASTM D 3702 Modified |
| Dynamic COF                       | 0.5           | -                                               | ASTM D 3702 Modified |
| Static COF                        | 0.42          | -                                               | ASTM D 3702 Modified |
| Density                           | 1.57          | g/cm <sup>3</sup>                               | ISO 1183             |



## LNP™ LUBRICOMP™ Compound WFP36

### Americas: COMMERCIAL

| PROCESSING PARAMETERS       | TYPICAL VALUE | Unit |
|-----------------------------|---------------|------|
| <b>Injection Molding</b>    |               |      |
| Drying Temperature          | 120           | °C   |
| Drying Time                 | 4             | hrs  |
| Maximum Moisture Content    | 0.05          | %    |
| Melt Temperature            | 240 - 265     | °C   |
| Front - Zone 3 Temperature  | 260 - 270     | °C   |
| Middle - Zone 2 Temperature | 245 - 255     | °C   |
| Rear - Zone 1 Temperature   | 220 - 230     | °C   |
| Mold Temperature            | 80 - 100      | °C   |
| Back Pressure               | 0.2 - 0.3     | MPa  |
| Screw Speed                 | 30 - 60       | rpm  |