



LNP™ LUBRICOMP™ Compound WFL36E

Europe-Africa-Middle East: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound WFL-4036 EM
Product reorder name: WFL36E

LNP* LUBRICOMP* WFL36E is a compound based on Polybutyleneterephthalate resin containing Glass Fiber and PTFE. Added features include: Easy Molding and Wear Resistant. UL rating only applicable for color GY

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break, 5 mm/min	114	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.5	%	ISO 527
Tensile Modulus, 1 mm/min	10100	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	175	MPa	ISO 178
Flexural Stress, break, 2 mm/min	172	MPa	ISO 178
Flexural Strain, break, 2 mm/min	2.7	%	ISO 178
Flexural Modulus, 2 mm/min	9500	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	45	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	10	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	2.E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.2E-04	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	220	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	207	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow (5)	0.1 - 0.3	%	SABIC Method
Wear Factor Washer	24	10 ⁻⁴ -10 in ³ -min/ft-lb-hr	ASTM D 3702 Modified: Instr.
Dynamic COF	0.54	-	ASTM D 3702 Modified: Instr.
Static COF	0.58	-	ASTM D 3702 Modified: Instr.
Density	1.7	g/cm ³	ISO 1183
Water Absorption, 23°C/24hrs	0.04	%	ISO 62-1
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	1.5	mm	UL 94



LNP™ LUBRICOMP™ Compound WFL36E

Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.05	%
Melt Temperature	240 - 265	°C
Front - Zone 3 Temperature	260 - 270	°C
Middle - Zone 2 Temperature	245 - 255	°C
Rear - Zone 1 Temperature	220 - 230	°C
Mold Temperature	80 - 100	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm