



LNP™ STAT-KON™ Compound WEF42I

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound WCF-1006 HI

Product reorder name: WEF42I

LNP STAT-KON WEF42I is a compound based on PBT resin containing 10% Carbon Fiber, 20% Glass Fiber. Added features of this grade include: High Impact, Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	950	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1.7	%	ASTM D 638
Tensile Modulus, 50 mm/min	222700	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	1280	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	101800	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	99	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.5	%	ISO 527
Tensile Modulus, 1 mm/min	15830	MPa	ISO 527
Flexural Stress	169	MPa	ISO 178
Flexural Modulus, 2 mm/min	10520	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	72	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	12	cm-kgf/cm	ASTM D 256
Multiaxial Impact	45	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	169	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	45	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	14	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	219	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	205	°C	ASTM D 648
CTE, -30°C to 30°C, flow	2.1E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	1.34E-04	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	203	°C	ISO 75/Bf



LNP™ STAT-KON™ Compound WEF42I

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	220	°C	ISO 75/Af
PHYSICAL			
Density	1.44	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	0.3 - 0.5	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1 - 3	%	ASTM D 955
Density	1.44	g/cm ³	ISO 1183
ELECTRICAL			
Volume Resistivity	4.E+00 - 6.E+00	Ohm-cm	ASTM D 257
Surface Resistivity	2.E+00 - 5.E+00	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound WEF42I

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.05	%
Melt Temperature	240 - 265	°C
Front - Zone 3 Temperature	260 - 270	°C
Middle - Zone 2 Temperature	245 - 255	°C
Rear - Zone 1 Temperature	220 - 230	°C
Mold Temperature	80 - 100	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm