



LNP™ STAT-LOY™ Compound W3000XXJ

Americas: COMMERCIAL

Also known as: LNP™ STAT-LOY™ Compound W3000XXJ

Product reorder name: W3000XXJ

LNP STAT-LOY W3000XXJ is a compound based on PBT. Added features of this grade include: Anti-Stat, Colorable, Healthcare

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	410	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	4.3	%	ASTM D 638
Tensile Modulus, 50 mm/min	19700	kgf/cm ²	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	19700	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	42	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	8.5	%	ISO 527
Tensile Strain, break, 5 mm/min	9.6	%	ISO 527
Tensile Modulus, 1 mm/min	1880	MPa	ISO 527
Flexural Stress	61	MPa	ISO 178
Flexural Modulus, 2 mm/min	1890	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	142	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	6	cm-kgf/cm	ASTM D 256
Multiaxial Impact	8	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	37	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	89	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	157	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	55	°C	ASTM D 648
CTE, -30°C to 30°C, flow	1.15E-04	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	1.28E-04	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	139	°C	ISO 75/Bf



LNP™ STAT-LOY™ Compound W3000XXJ

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	54	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.27	-	ASTM D 792
Density	1.27	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.23	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	2 - 4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	2 - 4	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.37	%	ISO 62
ELECTRICAL			
Surface Resistivity	1.E+11 - 1.E+13	Ohm	ASTM D 257



LNP™ STAT-LOY™ Compound W3000XXJ

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	110	°C
Drying Time	4	hrs
Maximum Moisture Content	0.05	%
Melt Temperature	220 - 230	°C
Front - Zone 3 Temperature	220 - 230	°C
Middle - Zone 2 Temperature	215 - 225	°C
Rear - Zone 1 Temperature	205 - 215	°C
Mold Temperature	10 - 50	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm