



LNP™ THERMOCOMP™ Compound WF006

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound WF-1006

Product reorder name: WF006

LNP THERMOCOMP™ WF006 is a compound based on PBT resin containing 30% Glass Fiber.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1390	kgf/cm ²	ASTM D 638
Tensile Strain, break	2.9	%	ASTM D 638
Tensile Modulus, 50 mm/min	103700	kgf/cm ²	ASTM D 638
Flexural Stress	2260	kgf/cm ²	ASTM D 790
Flexural Modulus	95400	kgf/cm ²	ASTM D 790
Tensile Stress, break	133	MPa	ISO 527
Tensile Strain, break	2.5	%	ISO 527
Tensile Modulus, 1 mm/min	11180	MPa	ISO 527
Flexural Stress	208	MPa	ISO 178
Flexural Modulus	9100	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	85	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	9	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	115	cm-kgf	ASTM D 3763
Multiaxial Impact	21	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	51	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	9	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	222	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	207	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.11E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	3.11E-05	1/°C	ISO 11359-2



LNP™ THERMOCOMP™ Compound WF006

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, xflow	7.E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	221	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	202	°C	ISO 75/Af
PHYSICAL			
Density	1.559	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.05	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.3	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1.1	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.3	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	1.07	%	ISO 294
Density	1.55	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.07	%	ISO 62
FLAME CHARACTERISTICS			
UL Compliant, 94HB Flame Class Rating (3)(4)	1.5	mm	UL 94 by SABIC-IP



LNP™ THERMOCOMP™ Compound WF006

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.05	%
Melt Temperature	240 - 265	°C
Front - Zone 3 Temperature	260 - 270	°C
Middle - Zone 2 Temperature	245 - 255	°C
Rear - Zone 1 Temperature	220 - 230	°C
Mold Temperature	80 - 100	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm