



LNP™ THERMOCOMP™ Compound WX93111

Europe-Africa-Middle East: COMMERCIAL

LNP THERMOCOMP WX93111 is a compound based on Polybutylene Terephthalate resin containing Flame retardant , Glass Fiber, Proprietary filler. Added features include : Improved CTI.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break, 5 mm/min	43	MPa	ISO 527
Tensile Strain, break, 5 mm/min	0.6	%	ISO 527
Tensile Modulus, 1 mm/min	8900	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	244	MPa	ISO 178
Flexural Modulus, 2 mm/min	8900	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	4	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	3.4E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	7.7E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	135	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow (5)	0.3	%	SABIC Method
Density	1.8	g/cm ³	ISO 1183
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating (3)(4)	3	mm	UL 94 by SABIC-IP



LNP™ THERMOCOMP™ Compound WX93111

Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.05	%
Melt Temperature	245 - 260	°C
Front - Zone 3 Temperature	250 - 260	°C
Middle - Zone 2 Temperature	245 - 255	°C
Rear - Zone 1 Temperature	230 - 245	°C
Mold Temperature	80 - 100	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm