

VALOX™ FR RESINS 357M

REGION AMERICAS

DESCRIPTION

LIMITED USE, No New Customers / Applications as of Jan. 2010:

PBT+PC alloy with impact modifier and FR package for electrical markets. Extrusion Grade, Flame retardant, Impact Modified, Mold Release, Opaque, UL Grade,

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	48	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	48	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	82	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	82	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2060	MPa	ASTM D790
Hardness, Rockwell R	117	-	ASTM D785
IMPACT			
Izod Impact, unnotched, 23°C	3200	J/m	ASTM D4812
Izod Impact, notched, 23°C	530	J/m	ASTM D256
Gardner, 23°C	43	J	ASTM D3029
Modified Gardner, 23°C	43	J	ASTM D3029
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	137	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	98	°C	ASTM D648
CTE, -40°C to 40°C, flow	9.18E-05	1/°C	ASTM E831
CTE, 60°C to 138°C, flow	1.24E-04	1/°C	ASTM E831
Relative Temp Index, Elec	120	°C	UL 746B
Relative Temp Index, Mech w/impact	120	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
PHYSICAL			
Specific Gravity	1.34	-	ASTM D792
Specific Volume	0.75	cm ³ /g	ASTM D792
Water Absorption, (23°C/24hrs)	0.08	%	ASTM D570
Mold Shrinkage, flow, 0.75-2.3 mm	0.8 – 1.1	%	SABIC method
Mold Shrinkage, flow, 2.3-4.6 mm	1 – 1.4	%	SABIC method
Mold Shrinkage, xflow, 0.75-2.3 mm	0.9 – 1.3	%	SABIC method
Mold Shrinkage, xflow, 2.3-4.6 mm	1.2 – 1.6	%	SABIC method
ELECTRICAL			
Volume Resistivity	>1.2E+16	Ω.cm	ASTM D257
Dielectric Strength, in air, 3.2 mm	18.5	kV/mm	ASTM D149
Dielectric Strength, in oil, 1.6 mm	25.1	kV/mm	ASTM D149
Dielectric Strength, in oil, 3.2 mm	18.5	kV/mm	ASTM D149

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Relative Permittivity, 100 Hz	3.2	-	ASTM D150
Relative Permittivity, 1 MHz	3.2	-	ASTM D150
Dissipation Factor, 100 Hz	0.003	-	ASTM D150
Dissipation Factor, 1 MHz	0.03	-	ASTM D150
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D495
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	3	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-100036617	-	-
UL Yellow Card Link 2	E121562-220786	-	-
UL Recognized, 94HB Flame Class Rating	0.45	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	0.63	mm	UL 94
UL Recognized, 94-5VA Flame Class Rating	2.99	mm	UL 94
UV-light, water exposure/immersion	F2	-	UL 746C
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 265	°C	
Nozzle Temperature	245 – 260	°C	
Front - Zone 3 Temperature	250 – 265	°C	
Middle - Zone 2 Temperature	245 – 260	°C	
Rear - Zone 1 Temperature	240 – 255	°C	
Mold Temperature	50 – 75	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 100	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	