

# VALOX<sup>TM</sup> RESIN VX4910

REGION EUROPE

## DESCRIPTION

10% Glass reinforced nucleated PBT/ASA with excellent mechanical properties high dimensional stability, and low density.

## TYPICAL PROPERTY VALUES

| PROPERTIES                                   | TYPICAL VALUES | UNITS             | TEST METHODS |
|----------------------------------------------|----------------|-------------------|--------------|
| <b>MECHANICAL</b>                            |                |                   |              |
| Tensile Stress, yld, Type I, 5 mm/min        | 80             | MPa               | ASTM D 638   |
| Tensile Stress, brk, Type I, 5 mm/min        | 80             | MPa               | ASTM D 638   |
| Tensile Strain, yld, Type I, 5 mm/min        | 3              | %                 | ASTM D 638   |
| Tensile Strain, brk, Type I, 5 mm/min        | 3              | %                 | ASTM D 638   |
| Tensile Modulus, 5 mm/min                    | 4600           | MPa               | ASTM D 638   |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 115            | MPa               | ASTM D 790   |
| Flexural Stress, brk, 1.3 mm/min, 50 mm span | 115            | MPa               | ASTM D 790   |
| Flexural Modulus, 1.3 mm/min, 50 mm span     | 3400           | MPa               | ASTM D 790   |
| Tensile Stress, yield, 5 mm/min              | 80             | MPa               | ISO 527      |
| Tensile Stress, break, 5 mm/min              | 80             | MPa               | ISO 527      |
| Tensile Strain, yield, 5 mm/min              | 3              | %                 | ISO 527      |
| Tensile Strain, break, 5 mm/min              | 3              | %                 | ISO 527      |
| Tensile Modulus, 1 mm/min                    | 4600           | MPa               | ISO 527      |
| Flexural Stress, yield, 2 mm/min             | 120            | MPa               | ISO 178      |
| Flexural Stress, break, 2 mm/min             | 115            | MPa               | ISO 178      |
| Flexural Strain, break, 2 mm/min             | 4              | %                 | ISO 178      |
| Flexural Modulus, 2 mm/min                   | 3800           | MPa               | ISO 178      |
| Hardness, H358/30                            | 100            | MPa               | ISO 2039-1   |
| Hardness, Rockwell R                         | 120            | -                 | ISO 2039-2   |
| <b>IMPACT</b>                                |                |                   |              |
| Charpy Impact, unnotched, 23°C               | 45             | kJ/m <sup>2</sup> | ISO 179/2C   |
| Charpy Impact, unnotched, -30°C              | 20             | kJ/m <sup>2</sup> | ISO 179/2C   |
| Izod Impact, unnotched, 23°C                 | 440            | J/m               | ASTM D 4812  |
| Izod Impact, unnotched, -30°C                | 340            | J/m               | ASTM D 4812  |
| Izod Impact, notched, 23°C                   | 55             | J/m               | ASTM D 256   |
| Izod Impact, notched, 0°C                    | 50             | J/m               | ASTM D 256   |
| Izod Impact, notched, -30°C                  | 45             | J/m               | ASTM D 256   |
| Instrumented Impact Total Energy, 23°C       | 45             | J                 | ASTM D 3763  |
| Izod Impact, unnotched 80*10*4 +23°C         | 30             | kJ/m <sup>2</sup> | ISO 180/1U   |
| Izod Impact, unnotched 80*10*4 -30°C         | 25             | kJ/m <sup>2</sup> | ISO 180/1U   |
| Izod Impact, notched 80*10*4 +23°C           | 5              | kJ/m <sup>2</sup> | ISO 180/1A   |
| Izod Impact, notched 80*10*4 0°C             | 5              | kJ/m <sup>2</sup> | ISO 180/1A   |
| Izod Impact, notched 80*10*4 -30°C           | 5              | kJ/m <sup>2</sup> | ISO 180/1A   |
| Charpy Impact, notched, 23°C                 | 6              | kJ/m <sup>2</sup> | ISO 179/2C   |
| Charpy Impact, notched, -30°C                | 5              | kJ/m <sup>2</sup> | ISO 179/2C   |

| PROPERTIES                             | TYPICAL VALUES | UNITS      | TEST METHODS   |
|----------------------------------------|----------------|------------|----------------|
| THERMAL                                |                |            |                |
| Vicat Softening Temp, Rate A/50        | 218            | °C         | ASTM D 1525    |
| Vicat Softening Temp, Rate B/50        | 150            | °C         | ASTM D 1525    |
| HDT, 0.45 MPa, 3.2 mm, unannealed      | 205            | °C         | ASTM D 648     |
| HDT, 1.82 MPa, 3.2mm, unannealed       | 130            | °C         | ASTM D 648     |
| CTE, -40°C to 40°C, flow               | 4.11E-05       | 1/°C       | ISO 11359-2    |
| CTE, -40°C to 40°C, xflow              | 8.12E-05       | 1/°C       | ISO 11359-2    |
| CTE, 23°C to 60°C, flow                | 5.E-05         | 1/°C       | ISO 11359-2    |
| CTE, 23°C to 60°C, xflow               | 1.2E-04        | 1/°C       | ISO 11359-2    |
| CTE, 23°C to 150°C, flow               | 3.57E-05       | 1/°C       | ISO 11359-2    |
| CTE, 23°C to 150°C, xflow              | 1.96E-04       | 1/°C       | ISO 11359-2    |
| Ball Pressure Test, 125°C +/- 2°C      | PASSES         | -          | IEC 60695-10-2 |
| Vicat Softening Temp, Rate A/50        | 218            | °C         | ISO 306        |
| Vicat Softening Temp, Rate B/50        | 150            | °C         | ISO 306        |
| Vicat Softening Temp, Rate B/120       | 155            | °C         | ISO 306        |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm | 205            | °C         | ISO 75/Bf      |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm  | 130            | °C         | ISO 75/Af      |
| PHYSICAL                               |                |            |                |
| Specific Gravity                       | 1.3            | -          | ASTM D 792     |
| Filler Content                         | 10             | %          | ASTM D 229     |
| Mold Shrinkage, flow, 3.2 mm           | 0.6 – 0.8      | %          | SABIC method   |
| Melt Flow Rate, 200°C/3.8 kgf          | 20             | g/10 min   | ASTM D 1238    |
| Melt Flow Rate, 265°C/5.0 kgf          | 40             | g/10 min   | ASTM D 1238    |
| Density                                | 1.3            | g/cm³      | ISO 1183       |
| Melt Volume Rate, MVR at 250°C/5.0 kg  | 25             | cm³/10 min | ISO 1133       |
| Melt Volume Rate, MVR at 265°C/5.0 kg  | 35             | cm³/10 min | ISO 1133       |
| Melt Viscosity, 260°C, 1500 sec-1      | 160            | Pa-s       | ISO 11443      |
| ELECTRICAL                             |                |            |                |
| Relative Permittivity, 1 MHz           | 3.4            | -          | ASTM D 150     |
| Dissipation Factor, 1 MHz              | 0.02           | -          | ASTM D 150     |
| Relative Permittivity, 1 MHz           | 3.4            | -          | IEC 60250      |
| Dissipation Factor, 1 MHz              | 0.02           | -          | IEC 60250      |
| INJECTION MOLDING                      |                |            |                |
| Drying Temperature                     | 110 – 120      | °C         |                |
| Drying Time                            | 2 – 4          | hrs        |                |
| Maximum Moisture Content               | 0.02           | %          |                |
| Melt Temperature                       | 250 – 270      | °C         |                |
| Nozzle Temperature                     | 240 – 260      | °C         |                |
| Front - Zone 3 Temperature             | 245 – 265      | °C         |                |
| Middle - Zone 2 Temperature            | 240 – 255      | °C         |                |
| Rear - Zone 1 Temperature              | 230 – 245      | °C         |                |
| Hopper Temperature                     | 40 – 60        | °C         |                |
| Mold Temperature                       | 40 – 100       | °C         |                |