



VALOXTM RESIN VX4915R

REGION EUROPE

DESCRIPTION

15% Glass reinforced nucleated PBT/ASA improved release, with excellent mechanical properties high dimensional stability, and low density.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	85	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	85	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Modulus, 5 mm/min	5600	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	125	MPa	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	125	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	4200	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	80	MPa	ISO 527
Tensile Stress, break, 5 mm/min	80	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4	%	ISO 527
Tensile Strain, break, 5 mm/min	4	%	ISO 527
Tensile Modulus, 1 mm/min	5700	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	130	MPa	ISO 178
Flexural Stress, break, 2 mm/min	130	MPa	ISO 178
Flexural Strain, break, 2 mm/min	4	%	ISO 178
Flexural Modulus, 2 mm/min	4600	MPa	ISO 178
Hardness, H358/30	100	MPa	ISO 2039-1
Hardness, Rockwell R	120	-	ISO 2039-2
IMPACT			
Charpy Impact, unnotched, 23°C	45	kJ/m ²	ISO 179/2C
Charpy Impact, unnotched, -30°C	30	kJ/m ²	ISO 179/2C
Izod Impact, unnotched, 23°C	520	J/m	ASTM D 4812
Izod Impact, unnotched, -30°C	490	J/m	ASTM D 4812
Izod Impact, notched, 23°C	65	J/m	ASTM D 256
Izod Impact, notched, 0°C	60	J/m	ASTM D 256
Izod Impact, notched, -30°C	50	J/m	ASTM D 256
Izod Impact, unnotched 80*10*4 +23°C	35	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	25	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	6	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m ²	ISO 180/1A
Charpy Impact, notched, 23°C	6	kJ/m ²	ISO 179/2C
Charpy Impact, notched, -30°C	6	kJ/m ²	ISO 179/2C

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate A/50	213	°C	ASTM D 1525
Vicat Softening Temp, Rate B/50	135	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	200	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	105	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.29E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.22E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, flow	4.E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.E-04	1/°C	ISO 11359-2
CTE, 23°C to 150°C, flow	2.72E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	1.91E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	213	°C	ISO 306
Vicat Softening Temp, Rate B/50	135	°C	ISO 306
Vicat Softening Temp, Rate B/120	135	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	200	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	105	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.31	-	ASTM D 792
Filler Content	15	%	ASTM D 229
Mold Shrinkage on Tensile Bar, flow	0.2 – 0.6	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.3 – 0.7	%	SABIC method
Melt Flow Rate, 265°C/5.0 kgf	33	g/10 min	ASTM D 1238
Density	1.31	g/cm³	ISO 1183
Water Absorption, (23°C/sat)	0.8	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.3	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	20	cm³/10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	30	cm³/10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	155	Pa-s	ISO 11443
ELECTRICAL			
Volume Resistivity	>1.E+15	Ohm-cm	ASTM D 257
Dielectric Strength, in oil, 1.6 mm	22	kV/mm	ASTM D 149
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	ASTM D 149
Relative Permittivity, 1 MHz	3	-	ASTM D 150
Dissipation Factor, 1 MHz	0.02	-	ASTM D 150
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 1.6 mm	22	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3	-	IEC 60250
Dissipation Factor, 1 MHz	0.02	-	IEC 60250
Comparative Tracking Index	575	V	IEC 60112
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 270	°C	



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	245 – 265	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 245	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	