



VALOX™ Resin ENH4530

Europe-Africa-Middle East: COMMERCIAL

15% GF PBT, Non-Brominated & Non-Chlorinated Flame retardant

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	810	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	810	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Modulus, 5 mm/min	74400	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	1220	kgf/cm ²	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	1220	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	59100	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 5 mm/min	80	MPa	ISO 527
Tensile Stress, break, 5 mm/min	80	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2	%	ISO 527
Tensile Strain, break, 5 mm/min	3	%	ISO 527
Tensile Modulus, 1 mm/min	7500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	130	MPa	ISO 178
Flexural Stress, break, 2 mm/min	130	MPa	ISO 178
Flexural Strain, break, 2 mm/min	3	%	ISO 178
Flexural Modulus, 2 mm/min	6400	MPa	ISO 178
Hardness, H358/30	128	MPa	ISO 2039-1
Hardness, Rockwell R	98	-	ISO 2039-2
IMPACT			
Charpy Impact, unnotched, 23°C	35	kJ/m ²	ISO 179/2C
Charpy Impact, unnotched, -30°C	25	kJ/m ²	ISO 179/2C



VALOX™ Resin ENH4530

Europe-Africa-Middle East: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
IMPACT			
Izod Impact, unnotched, 23°C	40	cm-kgf/cm	ASTM D 4812
Izod Impact, unnotched, -30°C	36	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	5	cm-kgf/cm	ASTM D 256
Izod Impact, notched, 0°C	5	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -30°C	5	cm-kgf/cm	ASTM D 256
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	23	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	6	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	6	kJ/m ²	ISO 180/1A
Charpy Impact, notched, 23°C	6	kJ/m ²	ISO 179/2C
Charpy Impact, notched, -30°C	6	kJ/m ²	ISO 179/2C
THERMAL			
Vicat Softening Temp, Rate A/50	217	°C	ASTM D 1525
Vicat Softening Temp, Rate B/50	205	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	220	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	200	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.85E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, flow	4.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	1.73E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	220	°C	ISO 306
Vicat Softening Temp, Rate B/50	205	°C	ISO 306



VALOX™ Resin ENH4530

Europe-Africa-Middle East: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
Vicat Softening Temp, Rate B/120	205	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	220	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	200	°C	ISO 75/Af
Relative Temp Index, Elec	140	°C	UL 746B
Relative Temp Index, Mech w/impact	120	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
PHYSICAL			
Specific Gravity	1.45	-	ASTM D 792
Filler Content	15	%	ASTM D 229
Mold Shrinkage on Tensile Bar, flow (2) (5)	0.3 - 0.8	%	SABIC Method
Melt Flow Rate, 265°C/5.0 kgf	24	g/10 min	ASTM D 1238
Density	1.45	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.15	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.07	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	17	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	18	cm ³ /10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	150	Pa-s	ISO 11443
ELECTRICAL			
Volume Resistivity	1.E+15	Ohm-cm	ASTM D 257
Dielectric Strength, in oil, 0.8 mm	28	kV/mm	ASTM D 149
Dielectric Strength, in oil, 1.6 mm	21	kV/mm	ASTM D 149
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	ASTM D 149
Relative Permittivity, 1 MHz	3.7	-	ASTM D 150
Dissipation Factor, 1 MHz	0.15	-	ASTM D 150
Volume Resistivity	1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 0.8 mm	28	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	21	kV/mm	IEC 60243-1



VALOX™ Resin ENH4530

Europe-Africa-Middle East: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
ELECTRICAL			
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.7	-	IEC 60250
Dissipation Factor, 1 MHz	0.15	-	IEC 60250
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	0.8	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	3	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 3.0 mm	750	°C	IEC 60695-2-13



VALOX™ Resin ENH4530

Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	110 - 120	°C
Drying Time	2 - 4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	245 - 260	°C
Nozzle Temperature	230 - 255	°C
Front - Zone 3 Temperature	240 - 260	°C
Middle - Zone 2 Temperature	235 - 250	°C
Rear - Zone 1 Temperature	230 - 240	°C
Hopper Temperature	40 - 60	°C
Mold Temperature	40 - 100	°C