



VALOX™ Resin VC130
Asia Pacific: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	1690	kgf/cm ²	SABIC - Japan Method
Tensile Strain, break	3 - 3	%	SABIC - Japan Method
Flexural Stress	2430	kgf/cm ²	ASTM D 790
Flexural Modulus	178000	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	7	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	205	°C	ASTM D 648
CTE, -30°C to 30°C	5.E-05 - 5.E-05	1/°C	TMA
PHYSICAL			
Specific Gravity	1.5	-	ASTM D 792
Water Absorption, 24 hours	0.07	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm (5)	0.1 - 0.2	%	SABIC Method
Mold Shrinkage, flow, 6.4 mm (5)	0.6 - 0.7	%	SABIC Method
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	1.55	mm	UL 94