

Valox* Resin 420D

Americas: COMMERCIAL

30% GR, higher flow than 420. Ex. strength/stiffness/dimensional stability. High heat resistance. Appliance handles, spotlights, electrical motors...

Property

TYPICAL PROPERTIES ⁽¹⁾			
MECHANICAL	Value	Unit	Standard
Tensile Stress, brk, Type I, 5 mm/min	119	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	189	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	7580	MPa	ASTM D 790
Hardness, Rockwell R	118	-	ASTM D 785
IMPACT	Value	Unit	Standard
Izod Impact, unnotched, 23°C	801	J/m	ASTM D 4812
Izod Impact, notched, 23°C	85	J/m	ASTM D 256
THERMAL	Value	Unit	Standard
HDT, 0.45 MPa, 6.4 mm, unannealed	215	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	207	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.52E-05	1/°C	ASTM E 831
CTE, 60°C to 138°C, flow	2.52E-05	1/°C	ASTM E 831
PHYSICAL	Value	Unit	Standard
Specific Gravity	1.53	-	ASTM D 792
Specific Volume	0.65	cm ³ /g	ASTM D 792
Water Absorption, 24 hours	0.06	%	ASTM D 570
Mold Shrinkage, flow, 1.5-3.2 mm	0.3 - 0.5	%	SABIC Method
Mold Shrinkage, flow, 3.2-4.6 mm	0.5 - 0.8	%	SABIC Method
Mold Shrinkage, xflow, 1.5-3.2 mm	0.4 - 0.6	%	SABIC Method
Mold Shrinkage, xflow, 3.2-4.6 mm	0.6 - 0.9	%	SABIC Method
ELECTRICAL	Value	Unit	Standard
Volume Resistivity	>3.2E+16	Ohm-cm	ASTM D 257
Dielectric Strength, in air, 3.2 mm	18.7	kV/mm	ASTM D 149
Dielectric Strength, in oil, 1.6 mm	24.8	kV/mm	ASTM D 149
Relative Permittivity, 100 Hz	3.8	-	ASTM D 150
Relative Permittivity, 1 MHz	3.7	-	ASTM D 150
Dissipation Factor, 100 Hz	0.002	-	ASTM D 150
Dissipation Factor, 1 MHz	0.02	-	ASTM D 150
FLAME CHARACTERISTICS	Value	Unit	Standard
Oxygen Index (LOI)	19	%	ASTM D 2863

Processing

Parameter	Value	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	12	hrs

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)

Maximum Moisture Content	0.02	%
Melt Temperature	250 - 265	°C
Nozzle Temperature	245 - 260	°C
Front - Zone 3 Temperature	250 - 265	°C
Middle - Zone 2 Temperature	245 - 260	°C
Rear - Zone 1 Temperature	240 - 255	°C
Mold Temperature	65 - 90	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	50 - 80	rpm
Shot to Cylinder Size	40 - 80	%
Vent Depth	0.025 - 0.038	mm