



Valox* Resin 8024U

Europe-Africa-Middle East: COMMERCIAL

VALOX 8024U is a UV-stabilized, 20% glass fibre reinforced PBT+PET blend with excellent surface finish.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Taber Abrasion, CS-17, 1 kg	44	mg/1000cy	GE Method
Tensile Stress, break, 5 mm/min	120	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.8	%	ISO 527
Tensile Modulus, 1 mm/min	7000	MPa	ISO 527
Flexural Stress, break, 2 mm/min	175	MPa	ISO 178
Flexural Modulus, 2 mm/min	6500	MPa	ISO 178
Hardness, H358/30	135	MPa	ISO 2039-1
Hardness, Rockwell R	122	-	ISO 2039-2
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	31	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	31	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	8	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	7	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	8	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	7	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	35	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	33	kJ/m ²	ISO 179/1eU
THERMAL			
CTE, 23°C to 60°C, flow	3.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	203	°C	ISO 306
Vicat Softening Temp, Rate B/120	202	°C	ISO 306



Valox* Resin 8024U

Europe-Africa-Middle East: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
THERMAL			
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	215	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	190	°C	ISO 75/Ae
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow (2)	0.4 - 0.8	%	GE Method
Mold Shrinkage on Tensile Bar, xflow (2)	0.6 - 0.9	%	GE Method
Density	1.47	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.06	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.05	%	ISO 62
Melt Volume Rate, MVR at 265°C/1.2 kg	10	cm ³ /10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 3.2 mm	15	kV/mm	IEC 60243-1
Relative Permittivity, 50/60 Hz	3.3	-	IEC 60250
Relative Permittivity, 1 MHz	3.2	-	IEC 60250
Dissipation Factor, 50/60 Hz	0	-	IEC 60250
Dissipation Factor, 1 MHz	0.013	-	IEC 60250



Valox* Resin 8024U

Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	110 - 120	°C
Drying Time	4 - 6	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	260 - 285	°C
Nozzle Temperature	265 - 275	°C
Front - Zone 3 Temperature	260 - 280	°C
Middle - Zone 2 Temperature	255 - 280	°C
Rear - Zone 1 Temperature	240 - 260	°C
Hopper Temperature	40 - 60	°C
Mold Temperature	60 - 110	°C



Valox* Resin 8024U

Europe-Africa-Middle East: COMMERCIAL


CALCULATED FLOW LENGTH INDICATION

Moldflow® Radial Flow Analysis

Valox® 8024U

Melt Temperature : 260°C

Mold Temperature : 75°C



Note: Technical support is recommended if Gate Pressure is greater than 80 MPa. Contact your local representative.

© Moldflow is a registered trademark of the Moldflow Corporation.