

XENOY™ RESIN CL100

REGION EUROPE

DESCRIPTION

XENOY CL100 is an unfilled, impact modified, UV-stabilized PC/PBT blend with excellent solvent resistance and good low-temperature ductility. It has a proven track record in unpainted exterior automotive applications. ISO1043: PC+PBT-I.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	56	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	55	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	50	%	ASTM D638
Tensile Modulus, 5 mm/min	2200	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	85	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2050	MPa	ASTM D790
Taber Abrasion, CS-17, 1 kg	30	mg/1000cy	SABIC method
Tensile Stress, yield, 50 mm/min	55	MPa	ISO 527
Tensile Stress, break, 50 mm/min	56	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	50	%	ISO 527
Tensile Modulus, 1 mm/min	2150	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2050	MPa	ISO 178
Ball Indentation Hardness, H358/30	96	MPa	ISO 2039-1
IMPACT			
Izod Impact, notched, 23°C	700	J/m	ASTM D256
Izod Impact, notched, 0°C	600	J/m	ASTM D256
Izod Impact, notched, -30°C	170	J/m	ASTM D256
Izod Impact, notched, -40°C	160	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	50	J	ASTM D3763
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	50	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	45	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	20	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	55	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	20	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	125	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	90	°C	ASTM D648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, flow	9.E-05	1 / °C	ASTM E83 1
CTE, -40°C to 40°C, xflow	9.E-05	1 / °C	ASTM E83 1
Thermal Conductivity	0.18	W/m-°C	ISO 8302
CTE, 23°C to 80°C, flow	9.E-05	1 / °C	ISO 11359-2
CTE, 23°C to 80°C, xflow	9.E-05	1 / °C	ISO 11359-2
Vicat Softening Temp, Rate A/50	160	°C	ISO 306
Vicat Softening Temp, Rate B/50	125	°C	ISO 306
Vicat Softening Temp, Rate B/120	127	°C	ISO 306
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	90	°C	ISO 75 /Ae
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	110	°C	ISO 75 /Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	90	°C	ISO 75 /Af
PHYSICAL			
Specific Gravity	1.22	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.7 – 1	%	SABIC method
Melt Flow Rate, 250°C/5.0 kgf	14	g/10 min	ASTM D1238
Density	1.22	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.5	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	13	cm³/10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	>1.E+14	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, shorttime, 1.0mm	18	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.3	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.002	-	IEC 60250
Dissipation Factor, 1 MHz	0.02	-	IEC 60250
Relative Permittivity, 50/60 Hz	3.3	-	IEC 60250
FLAME CHARACTERISTICS			
UL Yellow Card Link	E45329-236630	-	-
UL Recognized, 94HB Flame Class Rating	1.5	mm	UL 94
INJECTION MOLDING			
Drying Temperature	90 – 100	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	255 – 270	°C	
Nozzle Temperature	250 – 265	°C	
Front - Zone 3 Temperature	250 – 270	°C	
Middle - Zone 2 Temperature	240 – 265	°C	
Rear - Zone 1 Temperature	230 – 250	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	60 – 80	°C	