

XENOY™ RESIN T2RX5230

ETP COMPOUND FROM TRUCIRCLE™ PORTFOLIO
REGION AMERICAS

DESCRIPTION

The grade is part of SABIC's TRUCIRCLE™ portfolio and services.

XENOY™ T2RX5230 is a 16% mineral filled PC/PET blend containing post-consumer recycle plastics. It has low CTE, high flow, high heat, dimensional stability, low shrinkage, especially for painted applications. XENOY™ T2RX5230 could be positioned for body panels, spoilers, housings, door handles, spring-loaded applications, fuel filler doors, medical device enclosures, EV electric vehicle components.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 5 mm/min	56	MPa	ISO 527
Tensile Stress, break, 5 mm/min	21	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.6	%	ISO 527
Tensile Strain, break, 5 mm/min	14	%	ISO 527
Tensile Modulus, 1 mm/min	3430	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	97	MPa	ISO 178
Flexural Modulus, 2 mm/min	4120	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	140	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	120	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m²	ISO 180/1A
THERMAL			
CTE, -30°C to 80°C, flow	4.2E-05	1/°C	ISO 11359-2
CTE, -30°C to 80°C, xflow	9.6E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	137	°C	ISO 306
Vicat Softening Temp, Rate B/120	140	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	100	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow	0.5 – 0.6	%	SABIC method
Mold Shrinkage, xflow	0.5 – 0.6	%	SABIC method
Density	1.34	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.42	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.14	%	ISO 62
Melt Volume Rate, MVR at 265°C/5.0 kg	24	cm³/10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	265 – 275	°C	
Nozzle Temperature	260 – 275	°C	
Front - Zone 3 Temperature	260 – 280	°C	



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Middle - Zone 2 Temperature	250 – 275	°C	
Rear - Zone 1 Temperature	240 – 270	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 100	°C	