



GELOY™ Resin HRA222F
Americas: COMMERCIAL

PC/ASA flame retardant, excellent weatherability.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	640	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	570	kgf/cm ²	ASTM D 638
Tensile Stress, yld, Type I, 5 mm/min	600	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	670	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4.3	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	>100	%	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4.2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	>100	%	ASTM D 638
Tensile Modulus, 5 mm/min	26400	kgf/cm ²	ASTM D 638
Tensile Stress, yield, 5 mm/min	62	MPa	ISO 527
Tensile Stress, break, 5 mm/min	51	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	60	MPa	ISO 527
Tensile Stress, break, 50 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4.3	%	ISO 527
Tensile Strain, break, 5 mm/min	>50	%	ISO 527
Tensile Strain, yield, 50 mm/min	4.4	%	ISO 527
Tensile Strain, break, 50 mm/min	>50	%	ISO 527
Tensile Modulus, 1 mm/min	2520	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	93	MPa	ISO 178
Flexural Modulus, 2 mm/min	2510	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	39	cm-kgf/cm	ASTM D 256



GELOY™ Resin HRA222F
Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
IMPACT			
Izod Impact, notched, 0°C	29	cm-kgf/cm	ASTM D 256
Izod Impact, notched 80*10*4 +23°C	17	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	12	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	9	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	15	kJ/m ²	ISO 179/1eA
THERMAL			
CTE, -30°C to 80°C, flow	6.9E-05	1/°C	ISO 11359-2
CTE, -30°C to 80°C, xflow	7.1E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7.5E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	111	°C	ISO 306
Vicat Softening Temp, Rate B/50	102	°C	ISO 306
Vicat Softening Temp, Rate B/120	104	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	99	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	88	°C	ISO 75/Ae
Relative Temp Index, Elec	90	°C	UL 746B
Relative Temp Index, Mech w/impact	90	°C	UL 746B
Relative Temp Index, Mech w/o impact	90	°C	UL 746B
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow (2) (5)	0.4 - 0.6	%	SABIC Method
Density	1.17	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.6	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.2	%	ISO 62
Melt Volume Rate, MVR at 260°C/2.16 kg	13	cm ³ /10 min	ISO 1133
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A



GELOY™ Resin HRA222F
Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
ELECTRICAL			
Comparative Tracking Index	600	V	IEC 60112
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	2	mm	UL 94
Oxygen Index (LOI)	29	%	ISO 4589
UV-light, water exposure/immersion	F1	-	UL 746C



GELOY™ Resin HRA222F

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80 - 90	°C
Drying Time	2 - 4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	230 - 270	°C
Nozzle Temperature	220 - 260	°C
Front - Zone 3 Temperature	230 - 270	°C
Middle - Zone 2 Temperature	220 - 260	°C
Rear - Zone 1 Temperature	200 - 230	°C
Hopper Temperature	60 - 80	°C
Mold Temperature	50 - 70	°C