

LEXAN™ EX1332T resin

聚碳酸酯

SABIC Innovative Plastics

挤压说明

Multiwall Sheet Extrusion Parameters:

- Adapter Temperature: 240 - 280 C
- Barrel - Zone 1 Temperature: 260 - 300 C
- Barrel - Zone 2 Temperature: 260 - 290 C
- Barrel - Zone 3 Temperature: 260 - 290 C
- Calibrator Temperature: 50 - 100 C
- Die Temperature: 240 - 300 C
- Drying Temperature: 120 C
- Drying Time: 2 - 4 hrs
- Hopper Temperature: 100 - 120 C
- Melt Temperature: 260 - 300 C