

# LEXANT™ RESIN XLS1110T

REGION EUROPE

## DESCRIPTION

LEXANT™ XLS1110T resin is a 35 MVR polycarbonate. Designed for automotive optical parts requiring excellent flow properties, very high transmission and color stability. AMECA listed for protected applications only.

## TYPICAL PROPERTY VALUES

| PROPERTIES                                  | TYPICAL VALUES | UNITS             | TEST METHODS   |
|---------------------------------------------|----------------|-------------------|----------------|
| <b>MECHANICAL</b>                           |                |                   |                |
| Taber Abrasion, CS-17, 1 kg                 | 10             | mg/1000cy         | SABIC method   |
| Tensile Stress, yield, 50 mm/min            | 61             | MPa               | ISO 527        |
| Tensile Stress, break, 50 mm/min            | 64             | MPa               | ISO 527        |
| Tensile Strain, yield, 50 mm/min            | 6              | %                 | ISO 527        |
| Tensile Strain, break, 50 mm/min            | 75             | %                 | ISO 527        |
| Tensile Modulus, 1 mm/min                   | 2350           | MPa               | ISO 527        |
| Flexural Stress, yield, 2 mm/min            | 90             | MPa               | ISO 178        |
| Flexural Modulus, 2 mm/min                  | 2300           | MPa               | ISO 178        |
| Ball Indentation Hardness, H358/30          | 127            | MPa               | ISO 2039-1     |
| <b>IMPACT</b>                               |                |                   |                |
| Izod Impact, unnotched 80*10*3 +23°C        | NB             | kJ/m <sup>2</sup> | ISO 180/1U     |
| Izod Impact, unnotched 80*10*3 -30°C        | NB             | kJ/m <sup>2</sup> | ISO 180/1U     |
| Izod Impact, notched 80*10*3 +23°C          | 57             | kJ/m <sup>2</sup> | ISO 180/1A     |
| Izod Impact, notched 80*10*3 -30°C          | 14             | kJ/m <sup>2</sup> | ISO 180/1A     |
| Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm  | 55             | kJ/m <sup>2</sup> | ISO 179/1eA    |
| Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm | 11             | kJ/m <sup>2</sup> | ISO 179/1eA    |
| Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm  | NB             | kJ/m <sup>2</sup> | ISO 179/1eU    |
| Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm | NB             | kJ/m <sup>2</sup> | ISO 179/1eU    |
| <b>THERMAL</b>                              |                |                   |                |
| Thermal Conductivity                        | 0.2            | W/m.°C            | ISO 8302       |
| CTE, 23°C to 80°C, flow                     | 7.E-05         | 1/°C              | ISO 11359-2    |
| Ball Pressure Test, 125°C +/- 2°C           | PASSES         | -                 | IEC 60695-10-2 |
| Vicat Softening Temp, Rate B/50             | 144            | °C                | ISO 306        |
| Vicat Softening Temp, Rate B/120            | 145            | °C                | ISO 306        |
| HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm     | 133            | °C                | ISO 75/Be      |
| HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm     | 122            | °C                | ISO 75/Ae      |
| Relative Temp Index, Elec                   | 130            | °C                | UL 746B        |
| Relative Temp Index, Mech w/impact          | 125            | °C                | UL 746B        |
| Relative Temp Index, Mech w/o impact        | 125            | °C                | UL 746B        |
| <b>PHYSICAL</b>                             |                |                   |                |
| Mold Shrinkage on Tensile Bar, flow         | 0.5 – 0.7      | %                 | SABIC method   |
| Density                                     | 1.2            | g/cm <sup>3</sup> | ISO 1183       |
| Water Absorption, (23°C/saturated)          | 0.35           | %                 | ISO 62-1       |
| Moisture Absorption (23°C / 50% RH)         | 0.15           | %                 | ISO 62         |

| PROPERTIES                                    | TYPICAL VALUES | UNITS                    | TEST METHODS      |
|-----------------------------------------------|----------------|--------------------------|-------------------|
| Melt Volume Rate, MVR at 250°C/ 1.2 kg        | 6              | cm <sup>3</sup> / 10 min | ISO 1133          |
| Melt Volume Rate, MVR at 300°C/ 1.2 kg        | 35             | cm <sup>3</sup> / 10 min | ISO 1133          |
| OPTICAL                                       |                |                          |                   |
| Light Transmission                            |                |                          |                   |
| Light Transmission, 2.54 mm                   | >90            | %                        | ASTM D1003        |
| Light Transmission, 5.0 mm                    | >89            | %                        | SABIC method      |
| Light Transmission, 150 mm                    | >82            | %                        | SABIC method      |
| Light Transmission, 2.54 mm, 420nm            | >88            | %                        | SABIC method      |
| Haze, 2.54 mm                                 | <0.5           | %                        | ASTM D1003        |
| Refractive Index                              | 1.586          | -                        | ISO 489           |
| ELECTRICAL                                    |                |                          |                   |
| Volume Resistivity                            | >1.E+15        | Ω.cm                     | IEC 60093         |
| Surface Resistivity, ROA                      | >1.E+15        | Ω                        | IEC 60093         |
| Dielectric Strength, in oil, 3.2 mm           | 17             | kV/mm                    | IEC 60243-1       |
| Relative Permittivity, 1 MHz                  | 2.7            | -                        | IEC 60250         |
| Dissipation Factor, 50/60 Hz                  | 0.001          | -                        | IEC 60250         |
| Dissipation Factor, 1 MHz                     | 0.01           | -                        | IEC 60250         |
| Comparative Tracking Index                    | 250            | V                        | IEC 60112         |
| Relative Permittivity, 50/60 Hz               | 2.7            | -                        | IEC 60250         |
| FLAME CHARACTERISTICS                         |                |                          |                   |
| UL Compliant, 94V-2 Flame Class Rating        | 0.8            | mm                       | UL 94 by SABIC-IP |
| Glow Wire Flammability Index 850°C, passes at | 1              | mm                       | IEC 60695-2-12    |
| Glow Wire Ignitability Temperature, 1.0 mm    | >875           | °C                       | IEC 60695-2-13    |
| Oxygen Index (LOI)                            | 25             | %                        | ISO 4589          |
| INJECTION MOLDING                             |                |                          |                   |
| Drying Temperature                            | 120            | °C                       |                   |
| Drying Time                                   | 2 – 4          | Hrs                      |                   |
| Maximum Moisture Content                      | 0.02           | %                        |                   |
| Melt Temperature                              | 280 – 300      | °C                       |                   |
| Nozzle Temperature                            | 270 – 290      | °C                       |                   |
| Front - Zone 3 Temperature                    | 280 – 300      | °C                       |                   |
| Middle - Zone 2 Temperature                   | 270 – 290      | °C                       |                   |
| Rear - Zone 1 Temperature                     | 260 – 280      | °C                       |                   |
| Hopper Temperature                            | 60 – 80        | °C                       |                   |
| Mold Temperature                              | 80 – 100       | °C                       |                   |