



LEXAN™ Resin 135
Americas: COMMERCIAL

General purpose low flow polycarbonate powder grade

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	630	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	660	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	>70	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	940	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	23800	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	NB	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	92	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	652	cm-kgf	ASTM D 3763
THERMAL			
Vicat Softening Temp, Rate B/50	154	°C	ASTM D 1525
HDT, 0.45 MPa, 6.4 mm, unannealed	137	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	132	°C	ASTM D 648
CTE, -40°C to 95°C, flow	6.84E-05	1/°C	ASTM E 831
Specific Heat	1.25	J/g-°C	ASTM C 351
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Density	1.19	g/cm ³	ASTM D 792
Water Absorption, equilibrium, 23C	0.35	%	ASTM D 570
Water Absorption, equilibrium, 100°C	0.58	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm (5)	0.5 - 0.7	%	SABIC Method
Melt Flow Rate, 300°C/1.2 kgf	3.5	g/10 min	ASTM D 1238
OPTICAL			
Light Transmission, 2.54 mm	88	%	ASTM D 1003
Haze, 2.54 mm	1	%	ASTM D 1003



LEXAN™ Resin 135
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	48	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	320 - 345	°C
Nozzle Temperature	315 - 340	°C
Front - Zone 3 Temperature	320 - 345	°C
Middle - Zone 2 Temperature	310 - 330	°C
Rear - Zone 1 Temperature	300 - 320	°C
Mold Temperature	80 - 115	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	40 - 70	rpm
Shot to Cylinder Size	40 - 60	%
Vent Depth	0.025 - 0.076	mm