



LEXAN™ Resin 943X

Americas: COMMERCIAL

LEXAN 943X is a UV stabilized medium flow impact modified injection molding (IM) grade. This resin offers UL94 V0 @ 1.5mm flame retardancy based on non-bromine, non-chlorine FR systems, low temperature ductility characteristics and excellent processability with opportunities for shorter IM cycle times compared to standard PC. LEXAN 943X resin is a product available in a wide range of opaque colors and may be an excellent candidate for a wide range of applications.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	590	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	610	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	130	%	ASTM D 638
Tensile Modulus, 50 mm/min	21400	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	900	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	21000	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 50 mm/min	55	MPa	ISO 527
Tensile Stress, break, 50 mm/min	60	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	125	%	ISO 527
Tensile Modulus, 1 mm/min	2100	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	85	MPa	ISO 178
Flexural Modulus, 2 mm/min	2200	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	81	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -30°C	66	cm-kgf/cm	ASTM D 256
Instrumented Impact Total Energy, 23°C	509	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	70	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	50	kJ/m ²	ISO 180/1A



LEXAN™ Resin 943X

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
IMPACT			
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	75	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	60	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	140	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	135	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	120	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.5E-05	1/°C	ASTM E 831
CTE, 23°C to 80°C, flow	7.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7.7E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/120	140	°C	ISO 306
Relative Temp Index, Elec	125	°C	UL 746B
Relative Temp Index, Mech w/impact	115	°C	UL 746B
Relative Temp Index, Mech w/o impact	120	°C	UL 746B
PHYSICAL			
Specific Gravity	1.18	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.4 - 0.8	%	SABIC Method
Mold Shrinkage, xflow, 3.2 mm (5)	0.4 - 0.8	%	SABIC Method
Melt Flow Rate, 300°C/1.2 kgf	10	g/10 min	ASTM D 1238
Density	1.19	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.35	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62



LEXAN™ Resin 943X
Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Melt Volume Rate, MVR at 300°C/1.2 kg	9	cm ³ /10 min	ISO 1133
ELECTRICAL			
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	ASTM D 149
Relative Permittivity, 50/60 Hz	2.95	-	ASTM D 150
Relative Permittivity, 1 MHz	2.9	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.0024	-	ASTM D 150
Dissipation Factor, 1 MHz	0.0085	-	ASTM D 150
Hot Wire Ignition {PLC}	1	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
Dielectric Strength, in oil, 3.2 mm	16	kV/mm	IEC 60243-1
Comparative Tracking Index	225	V	IEC 60112
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	1.5	mm	UL 94
UL Recognized, 94-5VA Rating (3)	3	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	825	°C	IEC 60695-2-13



LEXAN™ Resin 943X
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	48	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	295 - 315	°C
Nozzle Temperature	290 - 310	°C
Front - Zone 3 Temperature	295 - 315	°C
Middle - Zone 2 Temperature	280 - 305	°C
Rear - Zone 1 Temperature	215 - 295	°C
Mold Temperature	70 - 95	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	40 - 70	rpm
Shot to Cylinder Size	40 - 60	%
Vent Depth	0.025 - 0.076	mm

• NOTE: Back Pressure, Screw Speed, Shot to Cylinder Size and Vent Depth are only mentioned as general guidelines. These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.