



LEXAN™ Resin EXL9414T

Europe-Africa-Middle East: COMMERCIAL

LEXAN EXL9414T resin grade is a halogen-free flame retardant polycarbonate featuring transparency, -40 degree C ductility and UL-94 V0 rating for injection molding applications. Excellent impact combined with good flow, all transparent colorability for aesthetics and thin wall flame retradancy makes this product an excellent candidate for thin wall applications.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	580	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	600	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5.6	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	123.9	%	ASTM D 638
Tensile Modulus, 50 mm/min	22200	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	930	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	22200	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 50 mm/min	56	MPa	ISO 527
Tensile Stress, break, 50 mm/min	55	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5.4	%	ISO 527
Tensile Strain, break, 50 mm/min	108	%	ISO 527
Tensile Modulus, 1 mm/min	2300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	88	MPa	ISO 178
Flexural Modulus, 2 mm/min	2120	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	84	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -30°C	72	cm-kgf/cm	ASTM D 256
Instrumented Impact Total Energy, 23°C	764	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	65	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	55	kJ/m ²	ISO 180/1A



LEXAN™ Resin EXL9414T

Europe-Africa-Middle East: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
IMPACT			
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	70	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	60	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate A/50	138	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	120	°C	ASTM D 648
CTE, -40°C to 95°C, flow	6.7E-05	1/°C	ASTM E 831
CTE, -40°C to 95°C, xflow	8.E-05	1/°C	ASTM E 831
CTE, 23°C to 80°C, flow	6.7E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	8.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	138	°C	ISO 306
Vicat Softening Temp, Rate B/120	139	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	116	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.19	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.4 - 0.8	%	SABIC Method
Melt Flow Rate, 300°C/1.2 kgf	13	g/10 min	ASTM D 1238
Density	1.19	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.12	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.09	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	12	cm ³ /10 min	ISO 1133
OPTICAL			
Light Transmission at 2.0 mm	84	%	SABIC Method
Haze, 2mm	3	%	SABIC Method
FLAME CHARACTERISTICS			
UL Recognized, 94V-1 Flame Class Rating (3)	1.5	mm	UL 94



LEXAN™ Resin EXL9414T

Europe-Africa-Middle East: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	1.8	mm	UL 94
Oxygen Index (LOI)	35	%	ISO 4589



LEXAN™ Resin EXL9414T

Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	48	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	295 - 315	°C
Nozzle Temperature	290 - 310	°C
Front - Zone 3 Temperature	295 - 315	°C
Middle - Zone 2 Temperature	280 - 305	°C
Rear - Zone 1 Temperature	270 - 295	°C
Mold Temperature	70 - 95	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	40 - 70	rpm
Shot to Cylinder Size	40 - 60	%
Vent Depth	0.025 - 0.076	mm