



LEXAN™ Resin FXE154
Americas: COMMERCIAL

FDA compliant (color limited) PC. 2.5 MFR. Potable water/extrusion blowmoldable. ILLUMINATE special effects (fluorescent/edge glow colors).

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	630	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	660	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	7	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	940	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	23900	kgf/cm ²	ASTM D 790
Hardness, Rockwell R	118	-	ASTM D 785
Taber Abrasion, CS-17, 1 kg	10	mg/1000cy	ASTM D 1044
IMPACT			
Izod Impact, unnotched, 23°C	326	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	76	cm-kgf/cm	ASTM D 256
Falling Dart Impact (D 3029), 23°C	1728	cm-kgf	ASTM D 3029
THERMAL			
Vicat Softening Temp, Rate B/50	157	°C	ASTM D 1525
HDT, 0.45 MPa, 6.4 mm, unannealed	137	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	132	°C	ASTM D 648
CTE, -40°C to 95°C, flow	6.84E-05	1/°C	ASTM E 831
Specific Heat	1.25	J/g-°C	ASTM C 351
Thermal Conductivity	0.19	W/m-°C	ASTM C 177
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Specific Volume	0.83	cm ³ /g	ASTM D 792
Density	1.19	g/cm ³	ASTM D 792
Water Absorption, 24 hours	0.15	%	ASTM D 570



LEXAN™ Resin FXE154
Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Water Absorption, equilibrium, 23C	0.35	%	ASTM D 570
Water Absorption, equilibrium, 100°C	0.58	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm (5)	0.5 - 0.7	%	SABIC Method
Melt Flow Rate, 300°C/1.2 kgf	2.5	g/10 min	ASTM D 1238
OPTICAL			
Light Transmission, 2.54 mm	88	%	ASTM D 1003
Haze, 2.54 mm	1	%	ASTM D 1003
Refractive Index	1.586	-	ASTM D 542



LEXAN™ Resin FXE154

Americas: COMMERCIAL

• CAUTION: For production delays of two or more hours, reduce temperature setpoints to 150°C (300°F).

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Extrusion Blow Molding		
Drying Temperature	115 - 120	°C
Drying Time	4 - 6	hrs
Drying Time (Cumulative)	48	hrs
Maximum Moisture Content	0.02	%
Minimum Moisture Content	0.01	%
Melt Temperature (Parison)	265 - 275	°C
Barrel - Zone 1 Temperature	260 - 275	°C
Barrel - Zone 2 Temperature	260 - 275	°C
Barrel - Zone 3 Temperature	260 - 275	°C
Barrel - Zone 4 Temperature	260 - 275	°C
Adapter - Zone 5 Temperature	260 - 275	°C
Head - Zone 6 - Top Temperature	260 - 275	°C
Head - Zone 7 - Bottom Temperature	260 - 275	°C
Screw Speed	15 - 50	rpm
Mold Temperature	65 - 95	°C
Die Temperature	270 - 280	°C

- Purge with HDPE prior to changing screw, head, or die tooling and/or machine shutdown.
- 24:1 L:D low shear 2.5:1 compression ratio screw recommended. Screw design affects melt temperature. Screw speed -- 15-50 rpm suggested. Adjust actual rpm for desired output while maintaining desired melt temperature range.