



LEXAN™ Resin HPH4404
Americas: COMMERCIAL

High heat specialty polycarbonate. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO10993 or USP Class VI). EtO, steam, gamma and e-beam sterilizable.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	660	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	710	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	7	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	>112	%	ASTM D 638
Tensile Modulus, 5 mm/min	21400	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	960	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	22400	kgf/cm ²	ASTM D 790
Hardness, Rockwell M	85	-	ASTM D 785
Hardness, Rockwell R	122	-	ASTM D 785
Tensile Stress, yield, 50 mm/min	65	MPa	ISO 527
Tensile Stress, break, 50 mm/min	60	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	7	%	ISO 527
Tensile Strain, break, 50 mm/min	85	%	ISO 527
Tensile Modulus, 1 mm/min	2150	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	66	MPa	ISO 178
Flexural Modulus, 2 mm/min	2120	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	NB326	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	61	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -30°C	-12	cm-kgf/cm	ASTM D 256
Tensile Impact, Type S	588	cm-kgf/cm ²	ASTM D 1822
Falling Dart Impact (D 3029), 23°C	1519	cm-kgf	ASTM D 3029



LEXAN™ Resin HPH4404

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
IMPACT			
Instrumented Impact Total Energy, 23°C	1223	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	53	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	11	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	57	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	13	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	160	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	142	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.E-05	1/°C	ASTM E 831
Specific Heat	1.25	J/g-°C	ASTM C 351
Thermal Conductivity	0.21	W/m-°C	ASTM C 177
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	154	°C	ISO 306
Vicat Softening Temp, Rate B/120	155	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	125	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Specific Volume	0.83	cm ³ /g	ASTM D 792
Density	1.19	g/cm ³	ASTM D 792



LEXAN™ Resin HPH4404

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Water Absorption, 24 hours	0.16	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm (5)	0.6 - 0.8	%	SABIC Method
Melt Flow Rate, 300°C/1.2 kgf	6	g/10 min	ASTM D 1238
Melt Flow Rate, 330°C/2.16 kgf	30	g/10 min	ASTM D 1238
Density	1.2	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.16	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.35	%	ISO 62
Melt Volume Rate, MVR at 330°C/2.16kg	29	cm ³ /10 min	ISO 1133
OPTICAL			
Light Transmission, 2.54 mm	85	%	ASTM D 1003
Haze, 2.54 mm	1	%	ASTM D 1003
Refractive Index	1.6	-	ASTM D 542
ELECTRICAL			
Volume Resistivity	>2.6E+17	Ohm-cm	ASTM D 257
Dielectric Strength, in air, 3.2 mm	20.2	kV/mm	ASTM D 149
Relative Permittivity, 50/60 Hz	3.15	-	ASTM D 150
Relative Permittivity, 1 MHz	3	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.0012	-	ASTM D 150
Dissipation Factor, 100 Hz	0.024	-	ASTM D 150



LEXAN™ Resin HPH4404
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	48	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	295 - 315	°C
Nozzle Temperature	290 - 310	°C
Front - Zone 3 Temperature	295 - 315	°C
Middle - Zone 2 Temperature	280 - 305	°C
Rear - Zone 1 Temperature	270 - 295	°C
Mold Temperature	70 - 95	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	40 - 70	rpm
Shot to Cylinder Size	40 - 60	%
Vent Depth	0.025 - 0.076	mm