



**LEXAN™ Resin XHT5146**  
**Americas: COMMERCIAL**

XHT5146 is a high flow, high heat polycarbonate copolymer with a haze onset of 185C. It is available in a range of opaque colors.

| TYPICAL PROPERTIES <sup>1</sup>              | TYPICAL VALUE | Unit                | Standard    |
|----------------------------------------------|---------------|---------------------|-------------|
| <b>MECHANICAL</b>                            |               |                     |             |
| Tensile Stress, yld, Type I, 50 mm/min       | 810           | kgf/cm <sup>2</sup> | ASTM D 638  |
| Tensile Stress, brk, Type I, 50 mm/min       | 660           | kgf/cm <sup>2</sup> | ASTM D 638  |
| Tensile Strain, yld, Type I, 50 mm/min       | 7.5           | %                   | ASTM D 638  |
| Tensile Strain, brk, Type I, 50 mm/min       | 45            | %                   | ASTM D 638  |
| Tensile Modulus, 5 mm/min                    | 26500         | kgf/cm <sup>2</sup> | ASTM D 638  |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 1270          | kgf/cm <sup>2</sup> | ASTM D 790  |
| Flexural Modulus, 1.3 mm/min, 50 mm span     | 27000         | kgf/cm <sup>2</sup> | ASTM D 790  |
| Tensile Stress, yield, 50 mm/min             | 80            | MPa                 | ISO 527     |
| Tensile Stress, break, 50 mm/min             | 65            | MPa                 | ISO 527     |
| Tensile Strain, yield, 50 mm/min             | 7             | %                   | ISO 527     |
| Tensile Strain, break, 50 mm/min             | 45            | %                   | ISO 527     |
| Tensile Modulus, 1 mm/min                    | 2500          | MPa                 | ISO 527     |
| Flexural Stress, yield, 2 mm/min             | 120           | MPa                 | ISO 178     |
| Flexural Modulus, 2 mm/min                   | 2550          | MPa                 | ISO 178     |
| <b>IMPACT</b>                                |               |                     |             |
| Izod Impact, notched, 23°C                   | 8             | cm-kgf/cm           | ASTM D 256  |
| Izod Impact, notched, -30°C                  | 3             | cm-kgf/cm           | ASTM D 256  |
| Instrumented Impact Total Energy, 23°C       | 662           | cm-kgf              | ASTM D 3763 |
| Izod Impact, unnotched 80*10*3 +23°C         | NB            | kJ/m <sup>2</sup>   | ISO 180/1U  |
| Izod Impact, unnotched 80*10*3 -30°C         | NB            | kJ/m <sup>2</sup>   | ISO 180/1U  |
| Izod Impact, notched 80*10*3 +23°C           | 11            | kJ/m <sup>2</sup>   | ISO 180/1A  |
| Izod Impact, notched 80*10*3 -30°C           | 8             | kJ/m <sup>2</sup>   | ISO 180/1A  |



## LEXAN™ Resin XHT5146

### Americas: COMMERCIAL

| TYPICAL PROPERTIES <sup>1</sup>             | TYPICAL VALUE | Unit              | Standard       |
|---------------------------------------------|---------------|-------------------|----------------|
| <b>IMPACT</b>                               |               |                   |                |
| Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm  | 11            | kJ/m <sup>2</sup> | ISO 179/1eA    |
| Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm | 8             | kJ/m <sup>2</sup> | ISO 179/1eA    |
| Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm  | NB            | kJ/m <sup>2</sup> | ISO 179/1eU    |
| Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm | NB            | kJ/m <sup>2</sup> | ISO 179/1eU    |
| <b>THERMAL</b>                              |               |                   |                |
| Vicat Softening Temp, Rate B/50             | 190           | °C                | ASTM D 1525    |
| HDT, 0.45 MPa, 3.2 mm, unannealed           | 185           | °C                | ASTM D 648     |
| HDT, 1.82 MPa, 3.2mm, unannealed            | 174           | °C                | ASTM D 648     |
| CTE, -40°C to 40°C, flow                    | 6.E-05        | 1/°C              | ASTM E 831     |
| CTE, -40°C to 40°C, xflow                   | 6.E-05        | 1/°C              | ASTM E 831     |
| Thermal Conductivity @ 25 °C                | 0.2           | W/m-°C            | ASTM C 177     |
| CTE, -40°C to 40°C, flow                    | 7.E-05        | 1/°C              | ISO 11359-2    |
| CTE, -40°C to 40°C, xflow                   | 6.5E-05       | 1/°C              | ISO 11359-2    |
| Ball Pressure Test, 125°C +/- 2°C           | PASSES        | -                 | IEC 60695-10-2 |
| Ball Pressure Test, 165°C +/- 2°C           | PASSES        | -                 | IEC 60695-10-2 |
| Vicat Softening Temp, Rate B/50             | 190           | °C                | ISO 306        |
| Vicat Softening Temp, Rate B/120            | 190           | °C                | ISO 306        |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm      | 183           | °C                | ISO 75/Bf      |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm       | 170           | °C                | ISO 75/Af      |
| Metallized Haze Onset                       | 180           | °C                | SABIC Method   |
| <b>PHYSICAL</b>                             |               |                   |                |
| Specific Gravity                            | 1.2           | -                 | ASTM D 792     |
| Mold Shrinkage, flow, 3.2 mm (5)            | 0.6 - 0.95    | %                 | SABIC Method   |
| Melt Flow Rate, 330°C/2.16 kgf              | 16            | g/10 min          | ASTM D 1238    |
| Density                                     | 1.2           | g/cm <sup>3</sup> | ISO 1183       |



**LEXAN™ Resin XHT5146**

**Americas: COMMERCIAL**

| TYPICAL PROPERTIES <sup>1</sup>       | TYPICAL VALUE | Unit                    | Standard |
|---------------------------------------|---------------|-------------------------|----------|
| <b>PHYSICAL</b>                       |               |                         |          |
| Water Absorption, (23°C/sat)          | 0.5           | %                       | ISO 62   |
| Moisture Absorption (23°C / 50% RH)   | 0.25          | %                       | ISO 62   |
| Melt Volume Rate, MVR at 330°C/2.16kg | 15            | cm <sup>3</sup> /10 min | ISO 1133 |



**LEXAN™ Resin XHT5146**

**Americas: COMMERCIAL**

| PROCESSING PARAMETERS       | TYPICAL VALUE | Unit |
|-----------------------------|---------------|------|
| <b>Injection Molding</b>    |               |      |
| Drying Temperature          | 135           | °C   |
| Drying Time                 | 5 - 6         | hrs  |
| Drying Time (Cumulative)    | 48            | hrs  |
| Maximum Moisture Content    | 0.02          | %    |
| Melt Temperature            | 320 - 345     | °C   |
| Nozzle Temperature          | 315 - 340     | °C   |
| Front - Zone 3 Temperature  | 320 - 345     | °C   |
| Middle - Zone 2 Temperature | 310 - 335     | °C   |
| Rear - Zone 1 Temperature   | 300 - 325     | °C   |
| Mold Temperature            | 110 - 140     | °C   |
| Back Pressure               | 0.3 - 0.7     | MPa  |
| Screw Speed                 | 40 - 70       | rpm  |
| Shot to Cylinder Size       | 40 - 60       | %    |
| Vent Depth                  | 0.025 - 0.076 | mm   |