



LNP™ COLORCOMP™ Compound DX06407H

Americas: COMMERCIAL

Also known as: LNP™ COLORCOMP™ Compound D-1000 EM MR HC

Product reorder name: DX06407H

LNP COLORCOMP DX06407H is an unfilled Polycarbonate. Added features of this material include: Easy Molding, Mold Release, Healthcare

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	640	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	590	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	6.2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	94	%	ASTM D 638
Tensile Modulus, 5 mm/min	23900	kgf/cm ²	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	24400	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 5 mm/min	65	MPa	ISO 527
Tensile Stress, break, 5 mm/min	54	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	6.3	%	ISO 527
Tensile Strain, break, 5 mm/min	104	%	ISO 527
Tensile Modulus, 1 mm/min	2300	MPa	ISO 527
Flexural Stress	91	MPa	ISO 178
Flexural Modulus, 2 mm/min	2290	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	133	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	79	cm-kgf/cm	ASTM D 256
Multiaxial Impact	703	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	642	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	224	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	9	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	94	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	103	°C	ASTM D 648



LNP™ COLORCOMP™ Compound DX06407H

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	96	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	104	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Density	1.2	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	0.7 - 0.9	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1 - 3	%	ASTM D 955



LNP™ COLORCOMP™ Compound DX06407H

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm