



LNP™ COLORCOMP™ Compound HF1110RC

Americas: COMMERCIAL

COLORCOMP HF1110RC is a compound based on Polycarbonate resin. Added features include: High Flow, Mold Release. For use in thin wall lighting lenses, data storage components and safety eyewear lenses.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	630	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	660	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	120	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	940	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	23500	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	65	cm-kgf/cm	ASTM D 256
Tensile Impact, Type S	385	cm-kgf/cm ²	ASTM D 1822
Instrumented Impact Energy @ peak, 23°C	553	cm-kgf	ASTM D 3763
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	126	°C	ASTM D 648
Relative Temp Index, Elec	130	°C	UL 746B
Relative Temp Index, Mech w/impact	130	°C	UL 746B
Relative Temp Index, Mech w/o impact	130	°C	UL 746B
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.5 - 0.7	%	SABIC Method
Melt Flow Rate, 300°C/1.2 kgf	25	g/10 min	ASTM D 1238
OPTICAL			
Light Transmission, 2.54 mm	88	%	ASTM D 1003
Haze, 2.54 mm	1	%	ASTM D 1003
ELECTRICAL			
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	1	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A



LNP™ COLORCOMP™ Compound HF1110RC

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
FLAME CHARACTERISTICS UL Recognized, 94V-2 Flame Class Rating (3)	1.09	mm	UL 94



LNP™ COLORCOMP™ Compound HF1110RC

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	48	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	270 - 295	°C
Nozzle Temperature	265 - 290	°C
Front - Zone 3 Temperature	270 - 295	°C
Middle - Zone 2 Temperature	260 - 280	°C
Rear - Zone 1 Temperature	250 - 270	°C
Mold Temperature	70 - 95	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	40 - 70	rpm
Shot to Cylinder Size	40 - 60	%
Vent Depth	0.025 - 0.076	mm