



LNP™ LUBRICOMP™ Compound DFL28EG

Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound DFL-4028 EM MG

Product reorder name: DFL28EG

LNP™ LUBRICOMP™ DFL28EG is a compound based on Polycarbonate resin containing 40% Glass Fiber/Milled Glass and 10% PTFE. Added features of this material are: Wear Resistant, Easy Molding.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	1170	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	1170	kgf/cm ²	ASTM D 638
Tensile Strain, break	0	%	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	1.9	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1.9	%	ASTM D 638
Tensile Modulus, 50 mm/min	112300	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	1790	kgf/cm ²	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	1790	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	100500	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 5 mm/min	116	MPa	ISO 527
Tensile Stress, break, 5 mm/min	116	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	1.9	%	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	10180	MPa	ISO 527
Flexural Stress	174	MPa	ISO 178
Flexural Modulus, 2 mm/min	9780	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	65	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	12	cm-kgf/cm	ASTM D 256
Multiaxial Impact	48	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	202	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	40	kJ/m ²	ISO 180/1U



LNP™ LUBRICOMP™ Compound DFL28EG

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
IMPACT			
Izod Impact, notched 80*10*4 +23°C	12	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	141	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	140	°C	ASTM D 648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	141	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	139	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.62	-	ASTM D 792
Density	1.61	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.08	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.9 - 0.2	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.3 - 0.6	%	ASTM D 955
Wear Factor Washer	45	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Wear Factor Ring	2	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Dynamic COF	0.61	-	ASTM D 3702 Modified
Static COF	0.57	-	ASTM D 3702 Modified
Moisture Absorption (23°C / 50% RH)	0.12	%	ISO 62



LNP™ LUBRICOMP™ Compound DFL28EG

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm