



LNP™ LUBRICOMP™ Compound DFL34

Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound DFL-4034

Product reorder name: DFL34

LNP™ LUBRICOMP™ DFL34 is a compound based on Polycarbonate resin containing 20% Glass Fiber, 15% PTFE. Added feature of this material is: Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	980	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	970	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2.8	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	3.3	%	ASTM D 638
Tensile Modulus, 50 mm/min	70000	kgf/cm ²	ASTM D 638
Flexural Stress	1450	kgf/cm ²	ASTM D 790
Flexural Stress, yld, 1.3 mm/min, 50 mm span	1460	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	50000	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 5 mm/min	2	MPa	ISO 527
Tensile Stress, break, 5 mm/min	89	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	94	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2.9	%	ISO 527
Tensile Strain, break, 5 mm/min	3.5	%	ISO 527
Tensile Modulus, 1 mm/min	6500	MPa	ISO 527
Flexural Stress	153	MPa	ISO 178
Flexural Strain, break, 2 mm/min	-	%	ISO 178
Flexural Modulus, 2 mm/min	6010	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	79	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	17	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	229	cm-kgf	ASTM D 3763
Multiaxial Impact	76	cm-kgf	ISO 6603



LNP™ LUBRICOMP™ Compound DFL34

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	47	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	147	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	143	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.8E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.6E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	2.8E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.6E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	147	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	144	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.46	-	ASTM D 792
Density	1.46	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.11	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.2 - 0.4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.3 - 0.6	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.2 - 0.4	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.3 - 0.5	%	ISO 294
Wear Factor Washer	76	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Dynamic COF	0.52	-	ASTM D 3702 Modified
Static COF	0.67	-	ASTM D 3702 Modified
Density	1.46	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.16	%	ISO 62



LNP™ LUBRICOMP™ Compound DFL34

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm