



LNP™ LUBRICOMP™ Compound DL003P

Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound DL-4030 EP

Product reorder name: DL003P

LNP LUBRICOMP™ DL003P is a compound based on Polycarbonate resin containing 15% PTFE. Added features of this material include: Exceptional Processing, Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	520	kgf/cm ²	ASTM D 638
Tensile Stress, break	430	kgf/cm ²	ASTM D 638
Tensile Strain, yield	5.2	%	ASTM D 638
Tensile Strain, break	39.9	%	ASTM D 638
Tensile Modulus, 50 mm/min	24700	kgf/cm ²	ASTM D 638
Flexural Stress	840	kgf/cm ²	ASTM D 790
Flexural Modulus	21400	kgf/cm ²	ASTM D 790
Tensile Stress, yield	53	MPa	ISO 527
Tensile Stress, break	42	MPa	ISO 527
Tensile Strain, yield	5.3	%	ISO 527
Tensile Strain, break	22.6	%	ISO 527
Tensile Modulus, 1 mm/min	2330	MPa	ISO 527
Flexural Stress	83	MPa	ISO 178
Flexural Modulus	2020	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	NB	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	13	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	308	cm-kgf	ASTM D 3763
Multiaxial Impact	737	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	13	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	121	°C	ASTM D 648



LNP™ LUBRICOMP™ Compound DL003P

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, flow	5.94E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.02E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	6.1E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.16E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	121	°C	ISO 75/Af
PHYSICAL			
Density	1.28	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.1	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.7 - 0.9	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.9 - 1.1	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.7 - 0.9	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.9 - 1.1	%	ISO 294
Wear Factor Washer	60	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Dynamic COF	0.18	-	ASTM D 3702 Modified
Static COF	0.07	-	ASTM D 3702 Modified
Density	1.28	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.17	%	ISO 62



LNP™ LUBRICOMP™ Compound DL003P

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	300 - 315	°C
Front - Zone 3 Temperature	310 - 320	°C
Middle - Zone 2 Temperature	305 - 315	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm