



LNP™ LUBRICOMP™ Compound DP001E

Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound DL-4510 EM

Product reorder name: DP001E

LNP™ LUBRICOMP™ DP001E is a Polycarbonate base resin containing 5% PTFE/Silicone. Added features of this material include: Easy Molding, Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	550	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	450	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	6	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	38.4	%	ASTM D 638
Tensile Modulus, 50 mm/min	22800	kgf/cm ²	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	22700	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 5 mm/min	54	MPa	ISO 527
Tensile Stress, break, 5 mm/min	41	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	6	%	ISO 527
Tensile Strain, break, 5 mm/min	48.3	%	ISO 527
Tensile Modulus, 1 mm/min	2130	MPa	ISO 527
Flexural Stress	72	MPa	ISO 178
Flexural Modulus, 2 mm/min	2030	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	148	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	60	cm-kgf/cm	ASTM D 256
Multiaxial Impact	455	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	358	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	181	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	36	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	141	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	127	°C	ASTM D 648



LNP™ LUBRICOMP™ Compound DP001E

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -30°C to 30°C, flow	6.9E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	7.1E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	140	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	126	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.12	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.3 - 0.5	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.5 - 0.7	%	ASTM D 955
Wear Factor Washer	153	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Wear Factor Ring	0 - 0	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Dynamic COF	0.21	-	ASTM D 3702 Modified
Static COF	0.11	-	ASTM D 3702 Modified
Density	1.2	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.17	%	ISO 62



LNP™ LUBRICOMP™ Compound DP001E

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	300 - 315	°C
Front - Zone 3 Temperature	310 - 320	°C
Middle - Zone 2 Temperature	305 - 315	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm