



LNP™ LUBRICOMP™ Compound Lexan_LF1000

Asia Pacific: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	680	kgf/cm ²	SABIC - Japan Method
Tensile Strain, break	220 - 220	%	SABIC - Japan Method
Flexural Stress	850	kgf/cm ²	ASTM D 790
Flexural Modulus	21900	kgf/cm ²	ASTM D 790
Hardness, Rockwell R	118	-	ASTM D 785
IMPACT			
Izod Impact, notched, 23°C	17	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	136	°C	ASTM D 648
CTE, -30°C to 30°C	5.E-05 - 7.E-05	1/°C	TMA
PHYSICAL			
Specific Gravity	1.26	-	ASTM D 792
Water Absorption, 24 hours	0.15	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm (5)	0.5 - 0.7	%	SABIC Method
ELECTRICAL			
Surface Resistivity	1.E+16	Ohm	ASTM D 257
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	1.7	mm	UL 94