



LNP™ LUBRILOY™ Compound D2000AXH

Americas: COMMERCIAL

Also known as: LNP™ LUBRILOY™ Compound D2000AXH

Product reorder name: D2000AXH

LNP LUBRILOY™ D2000AXH is a compound based on Polycarbonate resin containing Proprietary Lubricant. Added features of this material include: Wear Resistant, Healthcare.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	540	kgf/cm ²	ASTM D 638
Tensile Stress, break	610	kgf/cm ²	ASTM D 638
Tensile Strain, yield	6.5	%	ASTM D 638
Tensile Strain, break	125.6	%	ASTM D 638
Tensile Modulus, 50 mm/min	18900	kgf/cm ²	ASTM D 638
Flexural Stress	840	kgf/cm ²	ASTM D 790
Flexural Modulus	21700	kgf/cm ²	ASTM D 790
Tensile Stress, yield	54	MPa	ISO 527
Tensile Stress, break	53	MPa	ISO 527
Tensile Strain, yield	6.2	%	ISO 527
Tensile Strain, break	138	%	ISO 527
Tensile Modulus, 1 mm/min	1980	MPa	ISO 527
Flexural Stress	78	MPa	ISO 178
Flexural Modulus	2130	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	NB	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	72	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	408	cm-kgf	ASTM D 3763
Multiaxial Impact	492	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	137	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	56	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	140	°C	ASTM D 648



LNP™ LUBRILOY™ Compound D2000AXH

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	126	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.41E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.38E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	7.42E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.38E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	140	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	126	°C	ISO 75/Af
PHYSICAL			
Density	1.17	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.13	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.7 - 0.9	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.8 - 1	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.7 - 0.9	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.8 - 1	%	ISO 294
Wear Factor Washer	60	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Dynamic COF	0.16	-	ASTM D 3702 Modified
Static COF	0.09	-	ASTM D 3702 Modified
Density	1.17	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.19	%	ISO 62
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	1.5	mm	UL 94



LNP™ LUBRILOY™ Compound D2000AXH

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	100	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 315	°C
Front - Zone 3 Temperature	305 - 315	°C
Middle - Zone 2 Temperature	300 - 310	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	65 - 95	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm