

LNP™ STAT-KON™ COMPOUND DEF13

DCF-1004
REGION ASIA

DESCRIPTION

LNP* Stat-kon* DEF13 is a compound based on Polycarbonate resin containing Glass Fiber, Glass Fiber, Carbon Fiber. Added features of this material include: Electrically Conductive.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break	118	MPa	ASTM D 638
Tensile Strain, break	4	%	ASTM D 638
IMPACT			
Izod Impact, notched, 23°C	106	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	144	°C	ASTM D 648
PHYSICAL			
Density	1.29	g/cm ³	ASTM D 792
ELECTRICAL			
Surface Resistivity	1.E+02 – 1.E+06	Ohm	ASTM D 257
MECHANICAL PROPERTIES			
Flexural modulus	8050	MPa	ISO 178/1A
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	305 – 325	°C	
Front - Zone 3 Temperature	320 – 330	°C	
Middle - Zone 2 Temperature	310 – 320	°C	
Rear - Zone 1 Temperature	295 – 305	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	