



LNP™ STAT-KON™ Compound DD0009P

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound D-EP V-1

Product reorder name: DD0009P

LNP STAT-KON™ DD0009P is a compound based on Polycarbonate resin containing Carbon Powder. Added features of this material include: Electrically Conductive, Exceptional Processing, Flame Retardant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	650	kgf/cm ²	ASTM D 638
Tensile Stress, break	550	kgf/cm ²	ASTM D 638
Tensile Strain, yield	4.8	%	ASTM D 638
Tensile Strain, break	10	%	ASTM D 638
Tensile Modulus, 50 mm/min	26700	kgf/cm ²	ASTM D 638
Flexural Stress	1040	kgf/cm ²	ASTM D 790
Flexural Modulus	28800	kgf/cm ²	ASTM D 790
Tensile Stress, yield	59	MPa	ISO 527
Tensile Stress, break	53	MPa	ISO 527
Tensile Strain, yield	4.4	%	ISO 527
Tensile Strain, break	9.5	%	ISO 527
Tensile Modulus, 1 mm/min	2800	MPa	ISO 527
Flexural Stress	102	MPa	ISO 178
Flexural Modulus	3000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	213	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	11	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	127	cm-kgf	ASTM D 3763
Multiaxial Impact	357	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	134	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	9	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	140	°C	ASTM D 648



LNP™ STAT-KON™ Compound DD0009P

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	130	°C	ASTM D 648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	128	°C	ISO 75/Af
PHYSICAL			
Density	1.29	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.13	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.8	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.8	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.78	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.8	%	ISO 294
Moisture Absorption (23°C / 50% RH)	0.23	%	ISO 62
ELECTRICAL			
Surface Resistivity	1.E+02 - 1.E+06	Ohm	ASTM D 257
FLAME CHARACTERISTICS			
UL Compliant, 94V-1 Flame Class Rating (3)(4)	1.5	mm	UL 94 by SABIC-IP



LNP™ STAT-KON™ Compound DD0009P

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm