



LNP™ STAT-KON™ Compound DE0029E

Asia Pacific: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound DC-1002 EM FR PB

Product reorder name: DE0029E

LNP STAT-KON* DE0029E is a compound based on Polycarbonate resin containing Carbon Fiber. Added features of this material include: Easy Molding. Flame Retardant, Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1120	kgf/cm ²	ASTM D 638
Tensile Strain, break	2.5	%	ASTM D 638
Tensile Modulus, 50 mm/min	84300	kgf/cm ²	ASTM D 638
Flexural Stress	1820	kgf/cm ²	ASTM D 790
Flexural Modulus	77300	kgf/cm ²	ASTM D 790
Tensile Stress, break	117	MPa	ISO 527
Tensile Strain, break	2.4	%	ISO 527
Tensile Modulus, 1 mm/min	7800	MPa	ISO 527
Flexural Stress	183	MPa	ISO 178
Flexural Modulus	8650	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	46	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	6	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	174	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	144	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	141	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.35E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	3.45E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	2.36E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	3.46E-05	1/°C	ISO 11359-2



LNP™ STAT-KON™ Compound DE0029E

Asia Pacific: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	139	°C	ISO 75/Af
PHYSICAL			
Density	1.26	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.16	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.1 - 0.3	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.2 - 0.4	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.06 - 0.32	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.29 - 0.43	%	ISO 294
Density	1.26	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.2	%	ISO 62
ELECTRICAL			
Surface Resistivity	1.E+01 - 1.E+06	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound DE0029E

Asia Pacific: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm