



LNP™ STAT-KON™ Compound DE006ER

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound DC-1006 EM MR

Product reorder name: DE006ER

LNP STAT-KON™ DE006ER is a compound based on Polycarbonate resin containing 30% Carbon Fiber. Added features of this material include: Easy Molding. Mold Release, Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1530	kgf/cm ²	ASTM D 638
Tensile Strain, break	1.8	%	ASTM D 638
Tensile Modulus, 50 mm/min	199600	kgf/cm ²	ASTM D 638
Flexural Stress	2250	kgf/cm ²	ASTM D 790
Flexural Modulus	148300	kgf/cm ²	ASTM D 790
Tensile Stress, break	148	MPa	ISO 527
Tensile Strain, break	1.8	%	ISO 527
Tensile Modulus, 1 mm/min	16700	MPa	ISO 527
Flexural Stress	226	MPa	ISO 178
Flexural Modulus	16500	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	49	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	7	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	97	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	32	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	143	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	141	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.71E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	2.79E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	2.71E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	2.78E-05	1/°C	ISO 11359-2



LNP™ STAT-KON™ Compound DE006ER

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	140	°C	ISO 75/Af
PHYSICAL			
Density	1.3	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.14	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.04 - 0.1	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.3 - 0.4	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.04 - 0.13	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.35 - 0.4	%	ISO 294
Density	1.3	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.21	%	ISO 62
ELECTRICAL			
Surface Resistivity	1.E+02 - 1.E+06	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound DE006ER

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm