



LNP™ STAT-KON™ Compound DEL139P

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound DCL-4013 EP FR

Product reorder name: DEL139P

LNP™ STAT-KON™ DEL139P is a compound based on Polycarbonate containing 15% Carbon Fiber, 5% PTFE. Added features of this grade include: Electrically Conductive, Exceptional Processing, Flame Retardant, Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	1280	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	1280	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Modulus, 50 mm/min	123100	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	1930	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	102100	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 5 mm/min	125	MPa	ISO 527
Tensile Stress, break, 5 mm/min	125	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	1.5	%	ISO 527
Tensile Strain, break, 5 mm/min	1.6	%	ISO 527
Tensile Modulus, 1 mm/min	13540	MPa	ISO 527
Flexural Modulus, 2 mm/min	9640	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	44	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	4	cm-kgf/cm	ASTM D 256
Multiaxial Impact	27	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	27	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	4	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	141	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	137	°C	ASTM D 648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	145	°C	ISO 75/Bf



LNP™ STAT-KON™ Compound DEL139P

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	140	°C	ISO 75/Af
PHYSICAL			
Density	1.34	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.12	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.12	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.49	%	ASTM D 955
Density	1.34	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.16	%	ISO 62
ELECTRICAL			
Surface Resistivity	1.E+02 - 1.E+06	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound DEL139P

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm