



LNP™ STAT-KON™ Compound DEL329EP

Europe-Africa-Middle East: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound STATKON-DCL-4032 FR

Product reorder name: DEL329EP

LNP STAT-KON DEL329EP is a compound based on Polycarbonate resin containing Carbon Fiber, PTFE, Flame Retardant. Added features include: Electrically Conductive, Internally Lubricated, Flame retardant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield, 5 mm/min	103	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.6	%	ISO 527
Tensile Modulus, 1 mm/min	8600	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	143	MPa	ISO 178
Flexural Strain, break, 2 mm/min	2.5	%	ISO 178
Flexural Modulus, 2 mm/min	7200	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	20	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	1.8E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	8.2E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	144	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	140	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow (5)	0.1 - 0.3	%	SABIC Method
Density	1.35	g/cm ³	ISO 1183
Water Absorption, 23°C/24hrs	0.22	%	ISO 62-1
ELECTRICAL			
Surface Resistivity	1.E+02 - 1.E+04	Ohm	ASTM D 257
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	1.5	mm	UL 94



LNP™ STAT-KON™ Compound DEL329EP

Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm